Chapter 11 / Capítulo 11

SAP Superintelligence Series
ISSN: 3046-4463
Volume 3 – Intelligent automation, AI systems, and digital engineering in oil-gas-chemical industries
ISBN of the complete work: 978-9915-9851-0-7
ISBN of this volume: 978-9915-704-05-0
DOI of the chapter: https://doi.org/10.62486/978-9915-9851-0-7_202642
Pages: 184-202

©2026 The authors. This is an open access article distributed under the terms of the Creative Commons Attribution (CC BY) 4.0 License.

ORIGINAL

Automation-Driven Exploration Meets Biopolymer Science: Converging Technologies Shaping the Future of Oil, Gas, and Chemical Engineering

La exploración impulsada por la automatización se une a la ciencia de los biopolímeros: tecnologías convergentes que configuran el futuro del petróleo, el gas y la ingeniería química

S. Dhamotharan[1] ✉, M. Muthukrishnan[2] ✉, N. Bharanidharan[1] ✉, M. Prince[1] ✉, M. Sabareesh[1] ✉, P. Prabhu[1] ✉, Rashad Ismibayli[3] ✉

[1]Department of Mechanical Engineering, KIT-Kalaignarkarunanidhi Institute of Technology. Kannampalayam, Coimbatore, Tamil Nadu, 641 402, India.

[2]Department of Mechanical Engineering, Christ the King Engineering College. Karamadai, Coimbatore, Tamil Nadu, 641 104, India.

[3]Azerbaijan University of Architecture and Construction. Baku, Azerbaijan.

Corresponding Author: S. Dhamotharan ✉

ABSTRACT

The oil, gas, and chemical industries' digital transformation is significantly changing the methods of finding, extracting, and managing subsurface resources. However, equally fast advancements in plant-derived, non-cellulosic biopolymers are opening up new possibilities for the development of sustainable materials in these industries that have been traditionally heavily reliant on natural resources. This research looks at the intersection of these two technology areas: one being the frontier of automation in the search process, and the other being the development of biopolymer engineering to demonstrate how their merger could affect the company's strategies in the future comprising operational, environmental, and materials-based aspects. Plant-based biopolymers have become the focus of attention due to the increased demand for sustainable and biodegradable materials as substitutes for petroleum-based polymers. To date, research on cellulose-based polymers is comprehensive, however, there is still a large potential for non-cellulosic plant biopolymers such as starch, lignin, pectin, hemicellulose, cutin, and plant-derived proteins and gums to be explored. In fact, these biopolymers offer distinct possibilities because they are not only easily available but also have different kinds of structures and can have varying properties. The biopolymers can be isolated from the leftover parts of the harvest, seeds, fruits, roots, and exudates, thus, providing a sustainable source of packaging, medical, textile, and agricultural materials. This review covers the chemistry, the extraction methods, and the material properties of the major non-cellulosic plant-based biopolymers. It examines in detail their mechanical, thermal, and barrier properties, as well as their biodegradability, recyclability, and functional limitations. Moreover, it moves modification methods and blending strategies to improve the performance of the industrial application. The article also talks about the issues of the mechanical performance, biodegradability, and the compatibility of these biopolymers that are facing most prominently. The paper ends with the discussion of present innovations and future possibilities to locate research gaps and facilitate the extensive use of non-cellulosic biopolymers in eco-friendly material fashioning.

Keywords: Advanced Automation; Oil and Gas Exploration; Real-Time Sensing, Non-Cellulosic

Biopolymers; Plant Proteins; Sustainable Bioplastics.

RESUMEN

La transformación digital de las industrias del petróleo, el gas y la química está cambiando significativamente los métodos de búsqueda, extracción y gestión de recursos del subsuelo. Sin embargo, los avances igualmente rápidos en biopolímeros no celulósicos de origen vegetal están abriendo nuevas posibilidades para el desarrollo de materiales sostenibles en estas industrias, que tradicionalmente han dependido en gran medida de los recursos naturales. Esta investigación analiza la intersección de estas dos áreas tecnológicas: una, la frontera de la automatización en el proceso de búsqueda, y la otra, el desarrollo de la ingeniería de biopolímeros, para demostrar cómo su fusión podría afectar las estrategias futuras de la empresa, abarcando aspectos operativos, ambientales y de materiales. Los biopolímeros de origen vegetal se han convertido en el foco de atención debido a la creciente demanda de materiales sostenibles y biodegradables como sustitutos de los polímeros derivados del petróleo. Hasta la fecha, la investigación sobre polímeros de celulosa es exhaustiva; sin embargo, aún existe un gran potencial para la exploración de biopolímeros vegetales no celulósicos como el almidón, la lignina, la pectina, la hemicelulosa, la cutina y las proteínas y gomas de origen vegetal. De hecho, estos biopolímeros ofrecen distintas posibilidades, ya que no solo son fáciles de conseguir, sino que también presentan diferentes tipos de estructuras y propiedades. Los biopolímeros pueden aislarse de restos de cosechas, semillas, frutos, raíces y exudados, lo que proporciona una fuente sostenible de materiales de embalaje, médicos, textiles y agrícolas. Esta revisión abarca la química, los métodos de extracción y las propiedades materiales de los principales biopolímeros vegetales no celulósicos. Examina en detalle sus propiedades mecánicas, térmicas y de barrera, así como su biodegradabilidad, reciclabilidad y limitaciones funcionales. Además, promueve métodos de modificación y estrategias de mezcla para mejorar el rendimiento de las aplicaciones industriales. El artículo también aborda los problemas más importantes relacionados con el rendimiento mecánico, la biodegradabilidad y la compatibilidad de estos biopolímeros. El artículo finaliza con un análisis de las innovaciones actuales y las posibilidades futuras para identificar lagunas en la investigación y facilitar el uso extensivo de biopolímeros no celulósicos en la fabricación de materiales ecológicos.

Palabras clave: Automatización Avanzada; Exploración de Petróleo y Gas; Detección en Tiempo Real, Biopolímeros no Celulósicos; Proteínas Vegetales; Bioplásticos Sostenibles.

INTRODUCTION

In response to these issues, one of the main factors that led to the global search for sustainable materials is the growing concern for the environment with respect to plastic waste and the limited nature of fossil fuel resources. Traditional petrochemical plastics are a major source of environmental degradation because they are not biodegradable and their production process is carbon-intensive, although they are also very versatile and cheap. This has led to the rise of biopolymers as the next generation of plastics, which are made from renewable sources and have advantages such as biodegradability, decreased carbon dioxide emissions, and less impact on the planet.[1,2,3,4,5]

Bioplastics based on cellulose have been broadly researched, however, biopolymers from non-cellulosic plants are a neglected resource which is still a highly potential new-matter category. Such are carbohydrate polymers derived from plants like starch, pectin, and hemicellulose, in addition to aromatic and proteinaceous compounds such as lignin and plant proteins. These

biopolymers have a broad variety of physico-chemical properties that open up their application in different areas such as packaging, biomedical devices, and agriculture.[6,7] Significantly, a large portion of these compounds are obtained from the remains of agricultural activities and the off-gases of the food industry, thus making a significant contribution to waste valorization and the implementation of the circular economy.[8,9,10,11,12,13,14]

This review is a comprehensive critical examination of the scientific research concerning biopolymers of plant origin from non-cellulosic sources. The study is centered on determining their structural features, methods of extraction and processing, property enhancements, and applications in the real world. Moreover, the article considers the environmental impacts, market trends, as well as the technological and regulatory obstacles that limit the availability of the product on a large scale. By emphasizing the present shortages and potential future opportunities, this article serves as a tool to facilitate the evolution and market entry of the materials of the biopolymer industry that are next in line and are environmentally friendly.[15,16,17,18,19,20]

The rapid automation of operations, the introduction of new sensors, and the application of data-driven decision support systems are changing the operational environment of oil, gas, and chemical industries in a profound way. Digital platforms integrating real-time geological data, autonomous drilling control, and predictive analytics are nowadays the primary means for improving subsurface characterization and lowering exploration uncertainty. Automated systems have generally been credited with increased operational precision and also reduced human exposure to hazardous conditions in the field, thus safety and process efficiency have been improved, as it has been pointed out by recent publications.[21,22] Such technological breakthroughs are supported by general industrial digitization trends, in which smart monitoring systems, machine-learning-enabled diagnostic capabilities, and adaptive control units are becoming the technological backbone of modern energy engineering. Given that exploration conditions are getting tougher and resource extraction requirements are becoming higher, automation-driven solutions allow energy companies to be more responsive and efficient.[23]

While the world is moving towards new technologies, the materials used for energy and chemicals are also changing dramatically due to the advancement of plant-derived biopolymers, in particular, non-cellulosic structures like lignin, hemicellulose derivatives, and resin-based macromolecules. These materials have a great potential to be used as the most eco-friendly alternatives for coatings, drilling additives, corrosion mitigation systems, and composite reinforcements, and their properties are becoming more and more competitive with those of conventional petroleum-derived polymers.[24,25] The changes in these materials from laboratory to real-world applications are also facilitated by the developments in polymer chemistry and processing technologies that have broadened the functional versatility and performance of bio-based materials.

Combining automation innovations with biopolymer science into a single framework may, thus, lead to the creation of new environmentally friendly engineering solutions—solutions that harmonize operational intelligence with the manufacture of less polluting materials specially designed for energy-intensive sectors. The coming together of these two worlds is a strong indication of a larger movement towards a sustainability-focused engineering discipline where efficiency, performance, and environmental aspects need to be addressed simultaneously.

METHOD

Classification of Plant-Based Biopolymers

Non-cellulosic plant-based biopolymers can be divided into different groups depending on their chemical structure, source, and polymer class. Such categorization aids in identifying their functions and their possible uses in the industry. In fact, they may be classified into three major groups: polysaccharides, proteins, and aromatic polymers based on their molecular structure. For instance, starch, pectin, and hemicellulose, which are polysaccharides, consist of sugar

monomers and are generally hydrophilic; this characteristic is the main reason for their ability to form a film and for their biodegradability. Non-cellulosic biopolymers may have different architectures such as linear, branched, or crosslinked depending on their polymer architecture. To illustrate, the amylose part of starch is linear, whereas amylopectin is branched, which affects their gelatinization and film-forming properties. The reason for pectin being able to gel is its highly branched structure whereas the tightly packed, crosslinked structure of lignin is the main source of its mechanical stiffness as well as its environmental resistance.[13,14]

Major Non-Cellulosic Biopolymers and Their Sources

Non-cellulosic plant-based biopolymers are diverse in terms of their source and their chemical nature. The biopolymers in question are generally the result of the consumption of carbohydrates, the structure, and the secondary metabolites of plants. Every single one has unique molecular features that determine its physical properties, the possibility of being processed, and its performance in the final application as can be seen in table 1.

Table 1. Comparative Overview of Non-Cellulosic Plant-Based Biopolymers[1-20]

Biopolymer	Primary Source	Structure Type	Key Properties	Applications
Starch	Tubers (potato, cassava), cereals (maize)	Polysaccharide (amylose (linear α-1,4-linked D-glucose) and amylopectin (branched α-1,4 and α-1,6 linkages	Biodegradable, thermoplastic, moisture sensitive	Bioplastics, packaging films, disposable cutlery
Lignin	Wood, agro-waste, aper/ pulp byproducts	Aromatic phenolic polymer made of three monolignols: p-coumaryl alcohol, coniferyl alcohol, and sinapyl alcohol	UV resistant, thermally stable, antioxidant, hydrophobic	Fillers, coatings, adhesives, carbon fibers
Pectin	Citrus peels, apple pomace	Heteropolysaccharide (galacturonic acid backbone)	Gel-forming, pH sensitive, biodegradable	Food packaging, drug delivery, wound dressings
Xylans	Hardwood and cereal straw	β-(1→4)-linked xylose backbone with side chains	Biodegradable, film-forming, water-soluble	Biodegradable films, drug delivery, edible coatings
Mannans	Softwood, legumes, konjac	Linear or branched ß-(1→4)-linked mannose	High water absorbency, gelling, emulsifying	Food stabilizers, drug carriers, paper sizing
Glucans	Barley, oats, fungal biomass	Mixed ß-(1→3)/ (1→4)-glucose linkages	Immunomodulatory, gel-forming, antioxidant	Biomedical coatings, controlled-release systems, wound healing
Cutin/ Suberin	Fruit skins (e.g., tomatoes), cork tissues	Lipid-based polyesters (hydroxy fatty acids)	Hydrophobic, microbial resistant, flexible	Water-repellent coatings, packaging layers
Soy Protein Isolate	Soybeans	Globular protein (glycinin, ß-conglycinin)	Good film-forming, biodegradable, high tensile strength	Edible films, packaging, adhesives, biomedical scaffolds

Wheat Gluten	Wheat endosperm	Gliadins and glutenins	Thermoplastic, elastic, water- and gas-barrier properties	Biodegradable packaging, agricultural films
Zein	Corn endosperm	Hydrophobic prolamin	Film-forming, glossy, oil-resistant, biodegradable	Coatings, drug delivery, microencapsulation
Guar Gum	Cyamopsis tetragonoloba seeds	Galactomannan polysaccharide	High viscosity, water-holding, emulsifying	Food thickener, paper, textiles, drilling fluids
Gum Arabic	Acacia tree exudates	Complex glycoprotein-polysaccharide mix	Soluble, low viscosity, film-forming, emulsifier	Beverages, pharmaceuticals, microencapsulation
Locust Bean Gum	Ceratonia siliqua seeds	Galactomannan polysaccharide	Thickening, stabilizing, heat resistance	Dairy products, biodegradable films, cosmetics
Castor Oil-Based Polyurethane	Castor seed oil	Triglyceride-derived polyol	Flexible, biodegradable, hydrophobic, good chemical resistance	Coatings, adhesives, foams, biomedical devices, packaging
Linseed Oil Alkyd Resin	Linum usitatissimum (flax)	Unsaturated fatty acid esters	Thermosetting, UV-stable, crosslinkable, eco-friendly	Surface coatings, paints, printing inks, plasticizers
Carnauba Wax Esters	Copernicia prunifera leaves	Long-chain aliphatic esters	High melting point, glossy finish, excellent water resistance	Food coatings, polishes, biodegradable films, cosmetics
Epoxidized Linseed Oil (ELO)	Linseed oil	Epoxidized triglycerides	Plasticizer, thermal stabilizer, flexible, low toxicity	Bioplasticizers in PVC, PLA, soy protein plastics
Hydroxylated Castor Oil Derivatives	Hydrogenated castor oil	Polyol-type	High hydroxyl functionality, rigidity, thermal resistance	Bio-foams, thermoset resins, renewable adhesives

Extraction and Processing Techniques

The quantity, and the usability of non-cellulosic biopolymers, then the most crucial factor would be their extraction and processing. Apart from enabling the isolation of polymers of high purity, the effective extraction methods also help in reducing the environmental load and making the process more economically viable. The ways to do it include not only the old-style chemically based methods but also the modern, green, and nanotechnology-assisted ones. No one method can be perfect in terms of all these parameters - efficiency, scalability, environmental impact, and cost, but rather a compromise has to be found.

Conventional Methods

Conventional extraction methods for non-cellulosic biopolymers, such as acid or alkali hydrolysis, wet milling, and pulping, have been the major choices because of their effectiveness and upscaling possibilities over the years (figure 1). Nevertheless, these procedures usually require the use of aggressive chemicals and result in large amounts of waste. Typically,

traditional extraction methods comprise the following chemical treatments:

a) Acid or alkali hydrolysis. Complex biomolecules are broken down to simpler ones by using acidic or basic solutions.

b) Solvent extraction. In this process, solvents dissolve the target compounds from the plant matrix (e.g., ethanol or hexane).

c) Precipitation. The target compound is removed from the solution by the addition of a precipitating agent (e.g., alcohol or salts).

Though these techniques are entrenched and deliver high yields, they raise significant issues about pollution, loss of bioactivity, and high energy consumption.[8,9]

Green and Eco-Friendly Techniques




Figure 1. Conventional Extraction Methods of Non-Cellulosic Biopolymers

Green extraction technologies have been developed to address the issues related to the environmental and health impacts of conventional extraction methods. The latest green extraction technologies developments are enzyme-assisted, ultrasound-assisted, and subcritical fluid methods which provide more eco-friendly alternatives with lower environmental impact (figure 2). These methods discussed in table 2 that the authors of the paper aim to lessen the usage of harmful chemicals, lower energy consumption, and keep the purity of the extracted compounds intact.[6,7]




Figure 2. Green Extraction Techniques for Non-Cellulosic Biopolymers

Table 2. Green Extraction Methods for Biopolymers and Natural Compounds[5,6,7,8,9,10,11,12,13,14,15]

Extraction Method	Principle	Advantages	Typical Applications
Supercritical Fluid Extraction (SFE)	Uses supercritical CO_2 at high pressure and temperature.	Solvent-free, selective, ideal for thermolabile compounds.	Essential oils, lipids, antioxidants
Microwave-Assisted Extraction (MAE)	Microwave energy heats solvent and plant matrix, causing cell wall disruption.	Fast, energy-efficient, reduced solvent use, high yield.	Polyphenols, flavonoids, alkaloids
Ultrasound-Assisted Extraction (UAE)	Ultrasound waves generate cavitation bubbles that break cell walls.	Low-temperature, rapid, improves mass transfer.	Proteins, antioxidants, plant metabolites
Enzyme-Assisted Extraction (EAE)	Enzymes degrade structural polymers in cell walls.	Mild conditions, eco-friendly, improved extraction yield.	Polysaccharides, proteins, phenolics
Subcritical Water Extraction (SWE)	Uses hot water (100–374°C) under pressure to stay in liquid form.	No toxic solvents, efficient for polar/semi-polar compounds.	Flavonoids, polyphenols, sugars
Pressurized Liquid Extraction (PLE)	Uses liquid solvents (e.g., ethanol, water) at high temp (50–200°C) and pressure.	Faster, uses less solvent, suitable for thermo-stable and some heat-sensitive compounds.	Phenolics, lipids, alkaloids, natural antioxidants

These methods lessen the requirement for damaging solvents, decrease the amount of energy needed, and increase selectivity. To illustrate, MAE has been done successfully to extract pectin and gums from fruit peels with the help of a more efficient process and a shorter time.

[3] Moreover, enzyme-assisted extraction is widely used for protein and hemicellulose recovery because it is performed under gentle conditions and the polymer is not damaged.[4] However, besides these benefits, the transition to a larger scale and the cost of operations are still the main drawbacks.

Use of Nanotechnology in Biopolymer Processing

Nanotechnology is an instrument of significant change, it is a leading factor that contributes the major functionality and the performance of plant-based biopolymers. One of the ways a reduction in weight limitation, which is not common in this area, is to create materials from non-cellulosic biopolymer fibers with mechanical power. The reason for this significant improvement is that certain research results have shown it to be practical by embedding nano-scaled fillers such as nanoclays, cellulose nanocrystals (CNCs), and nano-silica in a biopolymer matrix. In a word, these enhancements pave the way for biopolymers to be used in packaging, automotive, and biomedical fields.

In order to make an extraction process more efficient and selective, different routes involving Nanoscale Solvents and Nanoemulsion-Based Techniques are considered for the release and/or modification of bioactive compounds during processing. Nanoemulsions are defined as emulsions with a droplet size of 20–200 nm, and which are stabilized by surfactants. These systems allow enhanced solubility, bioavailability, and stability of hydrophobic compounds (e.g., plant oils, essential oils, flavonoids). Contrary to that, Nanoscale solvents can go through the structure of a cell at the nano level, form links with particular molecular bonds, and isolate the chosen biopolymers (like lignin, pectin, proteins) under gentle conditions. The table 3 provides a brief about nanoemulsion-based techniques, which use non-cellulosic biopolymers as emulsifiers or matrices, the methods of emulsification (e.g., high-shear homogenization, ultrasonication), targeted functionalities, and the possible applications in active packaging, crop protection, biosensing, and antimicrobial delivery systems.[1,2,3,4,5]

Table 3. Nanoemulsion-based techniques utilizing non-cellulosic biopolymers for Packaging, Agriculture, Antimicrobial, and Sensing (PAAiS) application

Biopolymer	Nanoemulsion Role	Functional Role / Application in PAAiS
Starch	Encapsulating matrix in oil-in-water nanoemulsions (with/ without protein carriers)	Packaging: Active films with antioxidant/ antimicrobial oils Agriculture: Controlled pesticide/nutrient delivery
Zein (Protein)	Forms hydrophobic nanocarriers for poorly water-soluble actives	Active Ingredient Systems: Delivery of nutraceuticals, essential oils, vitamins
Pectin	Acts as stabilizer and film former in nanoemulsion dispersions	Packaging: Antioxidant and antimicrobial films Active Ingredients: Carrier for curcumin or lycopene
Chitosan	Forms bioactive coatings with nanoemulsified essential oils	Packaging: Antimicrobial films Agriculture: Biodegradable pesticide carriers
Whey Protein	Stabilizes oil-in-water nanoemulsions in combination with starch or polysaccharides	Packaging: Edible films/coatings Active Ingredients: Encapsulation of probiotics or sensitive bioactives
Gum Arabic	Natural emulsifier and antioxidant carrier in nanoemulsions	Agriculture: Foliar application carrier Food/Packaging: Beverage and oil stabilization

One interesting application is the nanoencapsulation of plant oils with protein-starch matrices, which has been demonstrated as a viable solution in the case of active food packaging and drug delivery systems by shielding the sensitive substances and enabling their controlled

release.[6] Though these innovations extend the use of non-cellulosic biopolymers to different industries, mainly to the ones with high-value sectors, it has to be emphasized that the issues of regulations, toxicology, and environmental safety of nanomaterials posed as a result, are still the most challenging questions that require extensive research.

Challenges in Scalability of Biopolymer Extraction

The diagram depicts how automation technologies have become the leading factor in the modern oil and gas exploration processes, primarily through automated drilling rigs, real-time sensing, and advanced data-analysis platforms. Continuous monitoring of pressure, temperature, vibration, and formation properties is realized by automated drilling systems aided by sensor networks. These parameters provide rapid feedback to control units that modify drilling parameters with minimal human intervention. These smart systems are said to have proven their ability trim non-productive time, elevate safety and precision operational in difficult exploration environments, as pointed out in the latest studies on automation in energy systems.[21,22,23] The two-way arrows signify the data communication between the field-level devices and the central analytical units where machine learning and predictive models analyze the incoming data to take operational decisions.

Simultaneously the chart depicts the polymer science advancements in the field of bioplastics coming from plants and hence becoming the potential sustainable engineering contributors in the energy and chemical industries. Non-cellulosic biopolymers are one of the most exciting candidates for drilling fluids, corrosion inhibition, and environmentally safe material replacements that have been traditionally petrochemical polymers-based. The use of these materials in the exploration schedule is in line with the trend toward green and high-performance industrial materials, as documented in recent polymer science literature.[24,25] The convergence illustrated in the chart suggests a future technological ecosystem, where automated exploration systems and biopolymer innovations have an interdependent relationship that pave the ways for the clean energy age as shown in figure 3.




Figure 3. Converging automation technologies and plant-based biopolymers for next-generation oil, gas, and chemical engineering

Structure-Property Relationships

The structure-property relationship is essential when one wants to comprehend the performance and portability of non-cellulosic plant-based biopolymers. The chemical composition, molecular architecture, and functional groups of these polymers primarily dictate their thermal behavior, mechanical properties, barrier performance, and biodegradability. It is absolutely necessary to have a detailed knowledge of these correlations when it comes to adjusting biopolymers for specific industrial functions.[11,12,13,14,15,16]

One of the most glads of biocomposites can be plastics based on plasticized starch (thermoplastic starch, TPS), biodegradable materials, because of their renewability, low cost, and ease of processing. Nevertheless, starch in its native form must be plasticized, usually by water, glycerol, or sorbitol applied with heat and shear to starch which exhibits thermoplastic behavior. The reinforcements, thus, improve the composites' mechanical, thermal, and barrier properties to a great extent, especially when fiber–matrix adhesion is coupled with chemical treatments or compatibilizers. Extrusion, injection molding, and compression molding are the common manufacturing methods for TPS biocomposites, and the efficiency of these methods is dictated by the starch source, filler dispersion, and formulation parameters as shown in table 4.

Table 4. Comparative summary of structure–property relationships among selected non-cellulosic biopolymers

Biopolymer	Key Functional Groups	Crystallinity	Thermal Stability	Water Sensitivity	Mechanical Strength	Notable Traits	Ref
Starch	Hydroxyl	Medium-High	Moderate (150-200°C)	High	Moderate	Good film-former; brittle when dry	Avérous & Boquillon
Lignin	Phenolic, Methoxyl	Amorphous-Low	High (>200°C)	Low	High	UV resistant; rigid; antioxidant	Laurichesse et al.[10]
Pectin	Carboxyl, Ester	Low-Medium	Low-Moderate	High	Low-Moderate	Gelling; used in food/pharma	Thakur et al.[4]
Hemi-cellulose	Hydroxyl, Acetyl	Low	Low-Moderate	High	Low	Flexible; biodegradable	Ebringerová et al.[13]
Proteins	Amine, Carboxyl	Variable	Moderate	Moderate	Moderate	Edible films; pH sensitive	Gennadios et al.; Semenova et al.

RESULTS AND DISCUSSION

Thermal degradation analysis

Thermal degradation analysis is one of the key methods that help determine changes in heat resistance, decomposition and volatile product evolution of biopolymers. These are mainly TGA (Thermogravimetric Analysis) and DTG (Differential Thermo-gravimetry) techniques which show the different stages of the degradation, temperature at the maximum decomposition, and the amount of residual char which are very important parameters for the evaluation of biopolymer materials for high-temperature processing and various end-use applications. The thermal degradation of non-cellulosic biopolymers is different to a large extent depending

on their molecular structure as well as their origin. In the case of hemicellulose, it is highly branched and amorphous, therefore it breaks down at lower temperatures (~268 °C), releasing volatile compounds such as acetic acid and furfural. Cellulose, because of its high crystallinity, is decomposed at higher temperatures (~355 °C) with sharp DTG peaks and it produces levoglucosan and furans.

Table 5. Thermal Degradation Characteristics of Non-Cellulosic Biopolymers

Biopolymer	Main Source	Degradation Temp Range (°C)	Peak Degradation Temp (°C)	Major Volatiles / Products	Remarks	Ref
Hemi-cellulose	Agricultural residues	200–350	~268	Acetic acid, CO, CO_2, furfural	Degrades first due to branched, amorphous structure	Yang et al., 2007
Cellulose	Plant cell walls	315–400	~355	CO, CO_2, levoglucosan, furans	High crystallinity; sharp DTG peak; major pyrolysis fraction	Yang et al., 2007
Lignin	Wood, straw, bark	200–500+	280–370 (broad peaks)	Phenols, methane, CO_2, char	Broad, slow degradation; aromatic rings lead to high char yield	Yang et al., 2007
Pectin	Citrus, apple peels	180–300	220–260	Acetic acid, aldehydes, CO_2	Low stability due to ester groups and branching	Wong et al., 2013
Proteins	Soy, wheat, pea	200–350	280–320	NH_3, CO_2, H_2O, sulfur volatiles	Two-stage degradation: denaturation and chain scission	Jaziri et al., 2020
Starch	Corn, cassava, potato	250–350	~310	Water, CO_2, acetic acid, aldehydes	Moisture loss <150 °C; decomposes to sugars and volatiles	Zhang et al., 2005

Table 5 outlines thermal degradation characteristics of the chosen non-cellulosic biopolymers, which, among others, include temperature ranges for degradation, peak decomposition temperature, major volatiles released, and structural remarks.

Modification Strategies for Property Enhancement

Non-cellulosic biopolymers are environmentally friendly but usually have problems like poor processability, low durability, and weak mechanical properties. To make them more industrially feasible, numerous modification methods (figure 4) have been introduced to adjust and improve their functional features.

Blending with Other Polymers

One of the most popular ways to maintain mechanical flexibility, processability, and biodegradability is by mixing non-cellulosic biopolymers either with synthetic or natural polymers. As an example, starch is usually mixed with poly(lactic acid) (PLA), polycaprolactone (PCL), or polyethylene (PE) to make the material less brittle and to enhance the ability to

form a film.[6] Films made from proteins can be mixed with gelatin, chitosan, or pectin, a polysaccharide, to get more flexible films and those with better barrier properties. Such systems usually behave synergistically; however, compatibility and phase separation still dominate as the main problems, which can be solved by using compatibilizers or reactive extrusion methods.




Figure 4. Modification Strategies for property enhancement in Non-cellulosic biopolymers

Nanocomposite Formation

Incorporation of nanoscale fillers such as nanoclays, cellulose nanocrystals (CNCs), graphene oxide, and metal nanoparticles has become a very powerful tool to non-cellulosic biopolymers to enhance their mechanical strength, thermal stability, and barrier properties. Upon crosslinking, the combination of these nanoinserts leads to the creation of hybrid nanocomposite films with noticeably better structural and functional features in comparison with the unmodified ones. Besides the expanded application potential of biopolymers in the areas of biodegradable packaging, active coatings, and biomedical materials, this synergistic approach is also in line with the increasing demand for sustainable, high-performance alternatives to conventional plastics.[7]

As an illustration, CNC-starch nanocomposites have been able to achieve great improvements in tensile strength and water vapor barrier properties, thus opening the way for their application as green wrapping.[8] The introduction of graphene oxide into the pectin matrix results in the enhancement of the material's thermal stability and mechanical stiffness, which in turn allows it to be used for biomedical and structural purposes.[9] Similarly, metal nanoparticle–lignin composites, in particular, those kinds that have silver or zinc oxide nanoparticles, could be used in food packaging and wound healing materials due to their excellent antimicrobial and UV-blocking properties.[10] Besides, nanoclay filled hemicellulose films demonstrated enhanced gas barrier and mechanical properties which was attributed to the intercalated or exfoliated structures formed.[11] Few of the notable researches in Nanocomposite Applications in Non-Cellulosic Biopolymers is given in table 6.

Table 6. Examples of Nanocomposite Applications in Non-Cellulosic Biopolymers				
Biopolymer	**Nanofiller**	**Property Enhanced**	**Application**	**Ref**
Starch	Cellulose nanocrystals (CNCs)	Tensile strength, barrier properties	Biodegradable packaging	Zhao et al., 2020
Pectin	Graphene oxide (GO)	Thermal stability, rigidity	Biomedical films	Wang et al., 2018
Lignin	Silver nanoparticles	Antimicrobial activity	Active packaging	Naseer et al., 2020
Hemicellulose	Montmorillonite nanoclay	Gas barrier, mechanical properties	Coatings and films	Tang et al., 2017

Applications of Non-Cellulosic Biopolymers

Safe and sustainable crop production is promoted by the use of agricultural bioplastics, such as biopolymer-based hydrogels, and films that can be used for watering, seed coating, and fertilizer and pesticide-controlled release formulations and at the same time reducing runoff and improving soil health.[20] In the case of the coatings and adhesives industry, proteins, lignin, and natural gums are the materials used for the production of sustainable and water-resistant surfaces and binders with improved adhesion. The biopolymers are the substances that from the Construction and Textile Industries are transformed into bio-composites, insulation foams, flame-retardant coatings, and functional finishing with antibacteria or fire-resistant properties.[21] A comprehensive table delineating the prominent application sectors, functional roles, challenges, and examples of biocomposites is appended below table 8.

Table 8. Application Sectors of Non-Cellulosic Biopolymers				
Application Sector	**Key Biopolymers**	**Functional Role**	**Challenges**	**Biocomposite Examples**
Packaging	Starch, Pectin, Proteins	Biodegradable films, edible coatings, barrier layers	Moisture sensitivity, limited mechanical strength, shelf life	Starch/PVA/CNC films Pectin/fatty acid edible films
Biomedical	Pectin, Zein, Lignin	Drug delivery, tissue scaffolds, wound healing	Regulatory approval, sterilization, biocompatibility	Pectin-chitosan-AgNPs hydrogel Lignin/PVA nanofibers
Agriculture	Starch, Hemicellulose, Lignin	Mulch films, seed coatings, hydrogels	Cost, degradation rate control, mechanical fragility	Starch-lignin seed coatings Hemicellulose-chitosan hydrogel
Coatings / Adhesives	Lignin, Proteins, Natural Gums	Bio-binders, barrier coatings, primers	Bond strength, curing conditions, water resistance	Soy protein/lignin adhesive Gum arabic-lignin coatings
Construction / Textile	Lignin, Proteins, Pectin	Lightweight composites, flame retardants, hydrogels	Processability, durability, fire resistance	Lignin-hemp panels Zein flame-retardant coatings
Electronics / Sensors	Lignin, Pectin, Starch	Flexible substrates, biosensors, dielectric materials	Electrical conductivity, thermal stability	Lignin/PEDOT:PSS films

Energy Storage	Lignin, Hemicellulose	Binders in electrodes, conductive additives, supercapacitor materials	Conductivity, charge retention, compatibility	Lignin-derived carbon for Li-ion batteries
Food (Functional Use)	Pectin, Starch, Protein	Encapsulation, delivery systems, emulsion stabilization	Release control, sensory effects, stability	Pectin microcapsules for probiotics
Water Treatment	Lignin, Starch, Hemicellulose	Heavy metal adsorption, dye removal, antimicrobial filtration	Regeneration, swelling, selectivity	Lignin–magnetite nanocomposites for Cr(VI) removal

Integrated Performance Outcomes of Automation and Biopolymer Systems

The figure is 6 shows how automation technologies and biopolymer systems are the primary factors that influence the performance of the oil and gas operations of the future. In the upper left, automation systems—illustrated by robotic control—depict the fast-spreading use of advanced drilling platforms, real-time sensing arrays, and AI-enabled decision systems in exploration. These kinds of systems are more and more being engineered to provide greater responsiveness and operational efficiency by, among other things, constantly modifying drilling parameters based on the subsurface conditions that are monitored in real-time, a performance upgrade that is in line with the research results of Zahid et al. and Kadkhodaie et al. on intelligent subsurface monitoring and automated rig control.[21,22]

The arrows that connect the automation to the main outcome node show the ways in which the technologies lead to the enhancement of data reliability, the reduction of non-productive time, and the facilitation of safer operations in high-risk oilfield environments. On the contrary, the use of biopolymer systems draws attention to the future role of non-cellulosic plant-derived materials—like lignin and hemicellulose derivatives—as eco-friendly raw materials for the oil and chemical sectors.

The biopolymers are compatible with drilling fluids, corrosion-resistant coatings, and environmental mitigation, as evidenced by the latest polymer science research.[24,25] Their contribution to oilfield operations results in better environmental performance, lessening of material toxicity, and the safety of workers being facilitated, which is symbolized by the oil pumpjack icon that is the safety component's anchor in the diagram.

Thus, they demonstrate how automation and biopolymers flow into shared performance indicators—responsiveness, operational efficiency, compatibility, safety, and environmental impact—the diagram, in fact, shows a converging technological landscape that is going beyond this point. Such a convergence means that digital intelligence and sustainable material innovation would be the major determinants of future oil, gas, and chemical engineering systems, a trend that is also in line with the findings of other studies on digitalization in process industries.[23]

Future Perspectives and Research Gaps

In spite of the progress made in plant-based non-cellulosic bio polymeric materials, numerous significant issues still exist that hinder their long-term industrial application. The variability of raw materials in terms of moisture, chemical makeup, and molecular structure makes it difficult to standardize and achieve a consistent output. Research efforts should be directed toward establishing protocols for pre-processing and quality control in real-time so as to ensure the stability of input materials. On top of that, the question of the scalability is raised since most of the labscale methods involve the use of energy intensive or no environmentally friendly solvents.




Figure 6. Integrated performance outcomes linking automation, biopolymers, and oil-sector operations

The industrial applicability of the low-impact, industrial scale processes such as reactive extrusion, supercritical CO_2 blending, or enzymatic modification can be greatly enhanced by the local feasibility.[13] Environmental assessments are sometimes only based on perfect composting scenarios. There is a need for degradation that takes place under real conditions in the marine, landfill, and soil systems, as well as region-specific Life Cycle Assessments (LCA) that can provide information about sustainable deployment.

From a design standpoint, the natural bioactive additives (e.g., phenolics, essential oils, alginates) incorporated into the material can improve the functionality of that material; however, the additives should not hinder the biodegradability or the safety of the material. This implies that ecocompatible multifunctionalization strategies must be developed. Finally, the lack of representation of technoeconomic analysis is noticeable. The adoption of commercial technologies can be propelled to the next level by the presence of different tools such as life cycle costing, cost-benefit modeling, and industrial symbiosis frameworks working hand in hand with policy incentives and labeling standards.[15,16,17]

CONCLUSIONS

The combination of automation-driven exploration technologies with advances in non-cellulosic biopolymer science is a potential way to change the whole future of oil, gas, and chemical engineering. Automating drilling operations, implementing real-time sensing platforms, and upgrading intelligent control architectures are some of the ways through which the precision of operations is being enhanced, risks mitigated, and responsiveness to changes in complex field environments increased. Meanwhile, the next-generation plant-based biopolymers are opening up possibilities for the supply of sustainable materials with attractive chemical, thermal, and ecological characteristics that make them suitable for drilling fluids, corrosion prevention, and equipment protection. As a result, the synergy between these two technological areas might finally make it possible to have energy systems that are not only safer and more efficient but also more environmentally friendly, thereby ensuring that the sector is able to satisfy the growing performance requirements while making progress in the direction of sustainability of the environment.

Non-cellulosic plant-derived biopolymers as green alternatives to traditional petroleum-based plastics are very promising and have the potential to widely be used across various sectors like packaging, agriculture, construction, and biomedicine. Their structural and chemical differences—from simple polysaccharides such as starch and pectin to recalcitrant molecules (lignin, hemicellulose, plant proteins, gums, and oils)—provide an almost unlimited range of functionalities. Despite this, the issues of processing inefficiencies, environmental stability, and end-of-life management hamper their large-scale use.

Looking ahead, the non-cellulosic biopolymers' success in large-scale applications will depend on partnerships spanning across materials science, environmental sustainability, industrial design, and regulatory frameworks. Techno-economic evaluations, standardization, and life cycle analysis will be of utmost importance to facilitate the market entry of such products. These biopolymers, being aligned with the principles of eco-friendly production and circular economy, have the potential to become a significant part of the solution to the future environmental and resource challenges.

BIBLIOGRAPHIC REFERENCES

1. Hopewell J, Dvorak R, Kosior E. Plastics recycling: Challenges and opportunities. Philos Trans R Soc Lond B Biol Sci. 2009;364(1526):2115–26. https://doi.org/10.1098/rstb.2008.0311

2. Shen L, Haufe J, Patel MK. Product overview and market projection of emerging bio-based plastics: PRO-BIP 2009. Report for European Polysaccharide Network of Excellence (EPNOE) & European Bioplastics. 2020. https://doi.org/10.6100/IR643940

3. Reddy N, Yang Y. Biofibers from agricultural byproducts for industrial applications. Trends Biotechnol. 2005;23(1):22–7. https://doi.org/10.1016/j.tibtech.2004.11.002

4. Thakur VK, Thakur MK, Raghavan P. Progress in green polymer composites from lignin for multifunctional applications: A review. ACS Sustain Chem Eng. 2017;5(9):8321–31. https://doi.org/10.1021/acssuschemeng.7b01473

5. Buddrus J. Grundlagen der Organischen Chemie. Berlin: Walter de Gruyter; 2011. p. 797–844.

6. Sharma B, Malik P, Jain P. Waste valorization of agro-industrial biomass for sustainable bio-based materials. Environ Chem Lett. 2021;19(1):305–32. https://doi.org/10.1007/s10311-020-01084-9.

7. Bajpai P. Biotechnology for Pulp and Paper Processing. Springer; 2019. https://doi.org/10.1007/978-981-13-3780-1

8. Petersen K, Nielsen PV, Bertelsen G, Lawther M, Olsen MB, Nilsson NH, Mortensen G. Potential of biobased materials for food packaging. Trends Food Sci Technol. 1999;10(2):52–68. https://doi.org/10.1016/S0924-2244(99)00017-9

9. Shogren RL, Doane WM, Garlotta D, Lawton JW, Willett JL. Biodegradation of starch/polylactic acid/poly(hydroxyester-ether) composite bars in soil. Polym Degrad Stab. 1998;59(3):305–8. https://doi.org/10.1016/S0141-3910(97)00191-5

10. Laurichesse S, Avérous L. Chemical modification of lignins: Towards biobased polymers.

Prog Polym Sci. 2014;39(7):1266–90. https://doi.org/10.1016/j.progpolymsci.2013.11.004.

11. Thakur VK, Thakur MK, Raghavan P. Progress in green polymer composites from lignin for multifunctional applications: A review. ACS Sustain Chem Eng. 2017;5(9):8321–31. https://doi.org/10.1021/acssuschemeng.7b01473.

12. Yapo BM, Koffi KL. Yellow passion fruit rind—A potential source of low-methoxyl pectin. Food Chem. 2006;99(3):450–7. https://doi.org/10.1016/j.foodchem.2005.08.021

13. Ebringerová A, Heinze T. Xylan and xylan derivatives–biopolymers with valuable properties, 1. Naturally occurring xylans structures, procedures and properties. Macromol Rapid Commun. 2000;21(9):542–56. https://doi.org/10.1002/1521-3927(20000801)21:9<542::AID-MARC542>3.0.CO;2-7

14. Moreira LRS, Filho EXF. An overview of mannan structure and mannan-degrading enzyme systems. Appl Microbiol Biotechnol. 2008;79:165–78. https://doi.org/10.1007/s00253-008-1423-4

15. Vetvicka V, Vetvickova J. Physiological effects of different types of beta-glucan. Biomed Pap. 2011;155(2):195–204. https://doi.org/10.5507/bp.2011.025

16. Koshy RR, Somasundaram ST, Thomas S. Soy protein-based biopolymers for packaging applications. J Appl Polym Sci. 2015;132(45). https://doi.org/10.1002/app.42681

17. Wang Y, Cheng H, Wang W. Biodegradable packaging materials based on wheat gluten: Preparation, properties and performance. Ind Crops Prod. 2011;34(1):353–61. https://doi.org/10.1016/j.indcrop.2011.03.018

18. Lawton JW. Zein: A history of processing and use. Cereal Chem. 2002;79(1):1–18. https://doi.org/10.1094/CCHEM.2002.79.1.1

19. Mudgil D, Barak S, Khatkar BS. Guar gum: Processing, properties and food applications—A Review. J Food Sci Technol. 2014;51(3):409–18. https://doi.org/10.1007/s13197-011-0522-x

20. Ali BH, Ziada A, Blunden G. Biological effects of gum arabic: A review of some recent research. Food Chem Toxicol. 2009;47(1):1–8. https://doi.org/10.1016/j.fct.2008.07.001

21. Zahid A, Haq M, Al-Sarkhi A. Advances in automation and digital technologies for intelligent oil and gas exploration. J Pet Sci Eng. 2023;225:111402. https://doi.org/10.1016/j.petrol.2023.111402

22. Kadkhodaie A, Rezaee R, Asadi M. Real-time sensing and autonomous systems for improved subsurface characterization. Energy Explor Exploit. 2022;40(1):75–98. https://doi.org/10.1177/01445987211047832

23. Khan F, Butt FS, Imtiaz S. Digitalization and automation in process industries: Implications for safety and sustainability. Chem Eng Res Des. 2021;171:90–108. https://doi.org/10.1016/j.cherd.2021.05.033

24. Liu H, Thakur VK, Zhang X. Non-cellulosic plant biopolymers: Structure, chemistry, and emerging applications. Prog Polym Sci. 2023;140:101638. https://doi.org/10.1016/j.

progpolymsci.2023.101638

25. Aditiya HB, Goralski CT, Goh CS. Advances and challenges in lignin-derived polymers for sustainable industrial applications. Renew Sustain Energy Rev. 2022;160:112268. https://doi.org/10.1016/j.rser.2022.112268

FINANCING

None.

CONFLICT OF INTEREST

None.

AUTHORSHIP CONTRIBUTION

Conceptualization: S. Dhamotharan, M. Muthukrishnan, N. Bharanidharan, M. Prince, M. Sabareesh, P. Prabhu, Rashad Ismibayli.

Data curation: S. Dhamotharan, M. Muthukrishnan, N. Bharanidharan, M. Prince, M. Sabareesh, P. Prabhu, Rashad Ismibayli.

Formal analysis: S. Dhamotharan, M. Muthukrishnan, N. Bharanidharan, M. Prince, M. Sabareesh, P. Prabhu, Rashad Ismibayli.

Drafting - original draft: S. Dhamotharan, M. Muthukrishnan, N. Bharanidharan, M. Prince, M. Sabareesh, P. Prabhu, Rashad Ismibayli.

Writing - proofreading and editing: S. Dhamotharan, M. Muthukrishnan, N. Bharanidharan, M. Prince, M. Sabareesh, P. Prabhu, Rashad Ismibayli.