Chapter 05

Advanced composite materials, biopolymers, and additive manufacturing for oil-gas-chemical engineering
ISBN: 978-9915-704-06-7
DOI: 10.62486/978-9915-704-06-7.Ch05
Pages: 84-102

©2026 The authors. This is an open access book distributed under the terms of the Creative Commons Attribution (CC BY) 4.0 License.

3D Printing of Functional Materials and Smart Automation Systems: Integrated Technological Pathways for Modern Oil-Gas-Chemical Engineering

Impresión 3D de materiales funcionales y sistemas de automatización inteligentes: vías tecnológicas integradas para la ingeniería moderna del petróleo, el gas y los productos químicos

R. Saravanan[1], P. Prabhu[1], A. Joyal Christ[1], K. Haridharan[1], K. Surendhar[1], Christo Ananth[2]

[1]Department of Mechanical Engineering, Kalaignarkarunanidhi Institute of Technology, Kannampalayam, Coimbatore, Tamil Nadu, 641402, India.

[2]Faculty of Artificial Intelligence and Digital Technologies, Samarkand State University, Uzbekistan.

Corresponding author: R. Saravanan

ABSTRACT

The quick rise of 3D printing technology with functional materials has been the major factor to change the design and production practices in mechanical engineering one by one, which leads to new possibilities for component customization, weight reduction, and performance tailoring. At the same time, the oil, gas, and chemical industries are experiencing a major technological change that is going to be dominated by intelligent automation, data-driven decision systems, and digitally integrated operational workflows. The advantages of 3D printing for industrial use include little material waste, simple manufacturing, minimal human participation, minimal post-processing, and energy efficiency. In this study, we provide insights on the development of 3D printing, its history, current state, uses, and potential future directions. There is a detailed explanation of various materials that work with each sort of 3D printing procedure. Three different early-discovered yet widely utilized polymer-based 3D printing technologies in this paper for the production of polymeric products: stereolithography (SLA), selective laser sintering (SLS) and fused deposition modelling (FDM). The primary aim of this study is to relate polymer material-processproperties of three different 3D printing methods in order to provide a comparative view. In addition, the advanced material-process requirements for 4D printing with the use of these print methods are illustrated by the example of magneto-active polymers. On the whole, the paper discusses the various features of these printing methods and presents advice for selecting a suitable print material and a 3D printing method that would be most efficient for the intended applications based on polymeric materials. Besides that, it covers the implementation practices for 4D printing of polymer-based systems by the most advanced methodology. Recently, innovative 3D technologies with the use of new bio-based renewable materials have demonstrated promising outcomes for everyday applications, thus creating new opportunities for sustainable 3D printing in the future. This review is a report on the 3D printing of bio-based materials, direct or partial printing on textiles, etc., providing considerations, challenges, and future outlooks.

Keywords: Additive Manufacturing; 3D Printing Technologies; Functional Materials; Multi-Material Printing; Mechanical Engineering Applications.

RESUMEN

El rápido crecimiento de la tecnología de impresión 3D con materiales funcionales ha sido un factor determinante en la transformación progresiva de las prácticas de diseño y producción en la ingeniería mecánica, abriendo nuevas posibilidades para la personalización de componentes, la reducción de peso y la optimización del desempeño. Al mismo tiempo, las industrias del petróleo, gas y química están atravesando una profunda transformación tecnológica caracterizada por la automatización inteligente, los sistemas de toma de decisiones basados en datos y los flujos de trabajo operativos digitalmente integrados. Entre las ventajas de la impresión 3D para aplicaciones industriales se encuentran la reducción del desperdicio de material, la simplificación del proceso de fabricación, la mínima intervención humana, el reducido posprocesamiento y la eficiencia energética. En este estudio se presentan perspectivas sobre la evolución de la impresión 3D, su historia, estado actual, aplicaciones y posibles direcciones futuras. Asimismo, se ofrece una explicación detallada de los distintos materiales compatibles con cada tipo de proceso de impresión 3D. El trabajo analiza tres tecnologías tempranamente desarrolladas y ampliamente utilizadas basadas en polímeros para la producción de productos poliméricos: estereolitografía (SLA), sinterizado selectivo por láser (SLS) y modelado por deposición fundida (FDM). El objetivo principal del estudio es relacionar las propiedades material–proceso de estos tres métodos de impresión 3D con el fin de ofrecer una visión comparativa. Además, se ilustran los requisitos avanzados material–proceso para la impresión 4D utilizando estas técnicas, ejemplificados mediante polímeros magnetoactivos. En conjunto, el artículo analiza las características de estos métodos de impresión y proporciona recomendaciones para seleccionar el material y el método de impresión 3D más adecuados según la aplicación prevista basada en materiales poliméricos. También se abordan las prácticas de implementación más avanzadas para la impresión 4D en sistemas poliméricos. Recientemente, tecnologías innovadoras de impresión 3D que emplean nuevos materiales renovables de base biológica han mostrado resultados prometedores en aplicaciones cotidianas, generando nuevas oportunidades para una impresión 3D sostenible en el futuro. Esta revisión presenta un informe sobre la impresión 3D de materiales de origen biológico, la impresión directa o parcial sobre textiles, entre otros aspectos, analizando consideraciones, desafíos y perspectivas futuras.

Palabras clave: Fabricación Aditiva; Tecnologías de Impresión 3D; Materiales Funcionales; Impresión Multimaterial; Aplicaciones en Ingeniería Mecánica.

INTRODUCTION

The evolution of additive manufacturing over the past two decades has been driven not only by improvements in printing hardware but also by the rapid development of functional materials tailored for AM processes.[1,2,3,4,5] Early research focused mainly on geometric prototyping, but advancements in printable conductive composites, carbon-based inks, metal-particle suspensions,[6,7,8,9] dielectric elastomers, and piezoelectric polymers have transformed AM into a platform for producing structural components with integrated functionalities.[3,6,10,11,13,15] Multi-material printing technologies—including direct ink writing, jetting systems, digital light processing, and hybrid extrusion platforms—now enable precise spatial deposition of diverse materials, allowing the fabrication of parts that simultaneously perform mechanical, electrical, and sensing functions.[1,5,14,16] These developments have made it possible to manufacture smart components such as embedded strain-sensor networks, flexible conductive pathways, soft robotic actuators, and mechanically load-bearing structures with built-in monitoring features, marking a major shift from traditional single-material prototyping to fully integrated functional manufacturing.

[3,14] With these developments, additive manufacturing has become a central enabling technology across mechanical engineering domains, supporting the fabrication of lightweight architectures, mechanical metamaterials, functionally graded structures, and thermally optimized components. Modern processes such as selective laser melting, electron-beam melting, directed energy deposition, stereolithography, and digital light processing allow engineers to fabricate not only high-strength structural parts but also components with embedded electronic, thermal, or actuation capabilities.[1,4,5,7,8,12,16,17] Recent studies highlight AM-produced dielectric elastomer actuators for soft robotic mechanisms,[9,13] fully printed strain-sensing composites with tunable mechanical responses,[3,14] and conductive polymer materials suitable for flexible electronics and electromechanical systems.[14,20,21] At the same time, metal-based AM continues to advance aerospace and automotive components, heat exchangers, turbine elements, and biomedical implants through improved powder metallurgy, better microstructural control, and enhanced reliability.[7,12,17] Together, these innovations demonstrate how AM has expanded beyond shape fabrication to become a versatile platform for multifunctional, high-performance engineering systems. With the maturation of additive manufacturing in the late 2000s and early 2010s, research began shifting from purely geometric prototyping toward the creation of functional, multi-material components capable of electrical, mechanical, or thermal functionalities. This transition was accelerated by the development of printable conductive composites, carbon-based inks, metal nanoparticle formulations, and dielectric elastomers, which enabled AM to support multifunctional engineering parts such as strain sensors, soft actuators, and embedded electronics.[3,6,10,11,13,15] Multi-material processes including direct ink writing, inkjet printing, DLP photopolymerization, and hybrid extrusion systems now allow controlled spatial deposition of conductive, insulating, magnetic, and piezoelectric materials, enabling the fabrication of mechanically robust yet electronically active structures.[1,5,14,16] As a result, AM has become a powerful tool for producing next-generation components with built-in sensing, monitoring, and actuation capabilities that directly serve the needs of modern mechanical engineering systems.[3,14]

Today, 3D printing is widely used across mechanical engineering disciplines due to its ability to fabricate topology-optimized structures, metamaterials, lightweight lattices, thermal devices, and functionally graded materials with tailored properties. Advanced techniques such as selective laser melting, electron-beam melting, directed energy deposition, and vat photopolymerization enable not only structural components but also the integration of embedded sensors, dielectric actuators, thermal-management features, conductive networks, and wear-resistant graded layers within a single part.[1,4,5,7,8,12,16,17] Numerous studies report robust 3D-printed dielectric elastomer actuators for soft robotic applications,[9,13] high-performance strain sensors produced via polymer–carbon composite systems,[3,14] and direct printing of functional polymer composites for flexible electronics and mechanical systems.[14,20,21] Concurrently, metal- and ceramic-based AM continues to advance high-performance components such as turbine blades, heat exchangers, biomedical implants, and aerospace-grade structures, supported by improvements in powder metallurgy and process control.[7,12,17] Collectively, these innovations demonstrate how AM has evolved into a key enabling technology for integrated, high-performance mechanical engineering applications. The fusion of functional-material additive manufacturing and intelligent automation is radically changing engineering methods in the oil-gas-chemical industries. By 3D printing innovations, structurally strong, application-specific components can be made from high-performance polymers, metal alloys, and hybrid functional materials, thus opening the way for new possibilities in customized part design, rapid prototyping, and material efficiency.[23,25] Meanwhile, digital automation enhancements—mostly robotics, real-time sensing, and data-driven control—are changing the building, the monitoring, and the maintenance of oil and gas infrastructures.[24] Changes are mostly driven by the outcomes of implementation research that shows the

feasibility of additive manufacturing in high-stress oilfield environments and the effectiveness of automation in greatly improving operational precision and safety.[21,22] In brief, these technological trends point to a large-scale transition to adaptive, digitally integrated engineering systems capable of meeting the tight performance requirements of the energy sectors of today.

3D printing has made end-use products available by manufacturing items that are not only structurally basic but also have sufficient mechanical support for the shape to be maintained. The 3D printing technology is getting better and is generating some low-volume, unpretentious 3D printed products. Today, the 3D printing development is a huge step far pharmaceutical and clinical organizations in writing more clear prescriptions, engaging in a rapid clinical installation process, and changing the way specialists and authorities prepare their strategies. Previously, medical 3D printing was only a powerful, ridiculous idea, but time and experience have turned it into reality. Currently 3D printing technological advances are helping pharmaceutical companies and clinical associations to create clearer prescriptions and clinical inserts and also change the way professionals and experts organize their methods.

METHOD

This review was developed using a structured, multi-stage methodology to ensure comprehensive coverage of additive manufacturing (AM) technologies, functional materials, and their applications in mechanical engineering. The approach integrates systematic literature retrieval, selective filtering, thematic clustering, and comparative synthesis. Methods used in prior AM review studies [1,2,3,4,5] informed the structure adopted here. In oil and gas engineering, the Materials and Method section illustrates the role of additive manufacturing in supporting vital operations across the different stages of exploration, drilling, and production systems. The material choice is influenced by the harsh conditions of the oilfield, where parts have to resist high pressures, corrosive liquids, abrasive particulates, and large temperature variations. After determining the right functional materials, for instance, high-strength alloys, polymer composites, or corrosion-resistant composites, 3D printing makes it possible to quickly manufacture the complex toolsets that include custom nozzles, downhole components, sensor housings, and flow-control devices. Besides the manufacturing processes, the parts undergo certain steps in post-processing, for example, heat treatment and surface modification are necessary to guarantee the parts' longevity and compliance with industry safety standards. The final stage of execution is about using these improved, additively manufactured parts in local applications, which can vary from drilling rigs and pumping stations to pipeline monitoring units. Hence, this integrated scheme is not only cutting the maintenance intervals but also boosting the reliability and operating effectiveness in the present-day oil and gas production systems.



Figure 5.1. 3D printing Process – Pipeline Oil technology

Classification of Functional Materials in 3D Printing

Functional materials used in additive manufacturing can be broadly classified according to their physicochemical behaviour, performance characteristics, and compatibility with specific printing processes. In 3D printing, these materials are typically engineered to exhibit electrical, thermal, mechanical, or electromechanical responses that extend beyond conventional structural roles. Their classification has evolved significantly as printing technologies have advanced, particularly with the introduction of multi-material deposition and voxel-level control strategies.[5,15,16] One of the largest categories comprises polymer-based functional materials, which include photopolymers, thermoplastics, elastomers, and polymer composites. Photopolymer resins used in vat photopolymerization (SLA, DLP) can be chemically modified with nanoparticles, conductive fillers, or optical modifiers to yield tailored dielectric, optical, or sensing behaviour.[1,6,7] Direct ink writing (DIW) systems enable the use of elastomeric and rheologically tuned inks, including dielectric elastomers, ionogels, and soft actuator materials, which demonstrate high strain responses and excellent adaptability for soft robotics.[9,13,16] Polymer–carbon composites, commonly formulated with graphite, graphene, CNTs, or carbon black, represent another widely studied group due to their tunable electrical conductivity, making them suitable for printed sensors, circuits, and strain-responsive components.[10,11,14]

Classification of Additive Manufacturing Processes for Functional Materials

The suitability of additive manufacturing for functional material integration largely depends on the underlying printing process. Each process family imposes constraints on deposition physics, thermal history, material compatibility, and achievable resolution. Consequently, different AM processes exhibit varying capacities to fabricate components with embedded sensing, actuation, optical, or electromechanical functionalities. Several comprehensive reviews have emphasized that understanding process–material interactions is essential for selecting the appropriate AM technology for specific functional applications as depicted in figure 5.2.[1,2,5,7]



Figure 5.2. Classification of Additive Manufacturing Processes for Functional Materials

Table 5.1. Classification of Major AM Processes Used for Functional Materials

AM Process Family	Typical Materials	Functional Capabilities	Key Advantages	Limitations	Supporting References
Vat Photopolymerization (SLA, DLP, CLIP)	Photopolymers, nanoparticle-filled resins	Optical microstructures, dielectric components, microfluidics	Very high resolution	Material-limited systems	(1,6,7,19)
Material Extrusion (FDM/FFF)	Thermoplastics, polymer–carbon composites	Conductive pathways, embedded wiring	Low cost, easy handling	Lower resolution	(10,11,14,17)
Direct Ink Writing (DIW)	Elastomers, hydrogels, conductive inks	Soft actuators, stretchable electronics	Multi-material & rheological flexibility	Slow deposition rate	(9,13,16)
Powder Bed Fusion (SLM, EBM, SLS)	Metals, ceramics, polymer powders	High-strength functional metallic parts	Excellent structural performance	High thermal load, expensive	(7,12,17,27)
Material Jetting / Inkjet AM	Nanoparticle inks, dielectric inks	Printed electronics, MEMS, thin-film circuits	High precision; true multi-material	Limited material viscosity	(2,10,23)
Directed Energy Deposition (DED)	Metals, metal-ceramic blends	Functionally graded materials	Large-scale builds; compositional grading	Lower resolution	(4,8,22)
Hybrid AM Systems	Polymers + metals + inks	Embedded sensors, integrated electronics	Combines strengths of multiple technologies	Complex operation	(5,15,30)

Among all AM categories, vat photopolymerization technologies—including stereolithography (SLA), digital light processing (DLP), and continuous liquid interface production (CLIP)—offer the highest geometric resolution and surface quality. Their ability to photopolymerize resin systems containing nanoparticles, conductive fillers, or dielectric additives has enabled microscale functional components, optical structures, and microfluidic devices.[1,6,7] Recent adaptations have demonstrated resin formulations designed for conductivity, high refractive index, or mechanical tunability, making vat photopolymerization particularly suitable for functional microdevices and optoelectronic elements.[6,7,19]

Material extrusion processes, notably fused deposition modeling (FDM) and direct ink writing (DIW), remain the most versatile for integrating functional materials. FDM commonly accommodates thermoplastic composites containing carbon-based fillers, metallic particles, or ceramic additives,[10,11,14] enabling economical manufacturing of embedded strain sensors, conductive networks, and mechanically robust prototypes. DIW, in contrast, exhibits superior compatibility with viscoelastic and rheologically complex inks, such as dielectric elastomers, hydrogels, ionogels, and multi-material conductive formulations.[9,13,16] This makes DIW a leading platform for soft actuators, printed electronics, and highly deformable electromechanical systems.

Powder bed fusion (PBF)—encompassing selective laser melting (SLM), electron beam melting (EBM), and selective laser sintering (SLS)—is widely used for functional metal and polymer components. Metallic PBF systems enable precise control over microstructure through melt-pool dynamics, laser power modulation, and build-parameter optimization, allowing production of high-performance structural components with excellent thermal conductivity and mechanical robustness.[7,12] PBF has also been used to fabricate heat exchangers, turbine components, and multifunctional metallic parts for aerospace and mechanical engineering applications.[12,17] SLS,

which typically processes polymer powders, has been used for durable functional housings, mechanical prototypes, and thermally stable components.[17]

Material jetting and inkjet-based AM represent another important class for functional material integration. These processes deposit droplets of nanoparticle inks, polymer solutions, or reactive precursors with extremely high spatial precision. They are particularly well suited for printed electronics, microelectromechanical systems (MEMS), and multilayered circuitry due to their capacity for depositing conductive, dielectric, and semiconductive materials in alternating layers.[2,10] Such processes have accomplished intricate device geometries, printed circuit paths, and thin-film functional architectures that are challenging to fabricate using other AM methods.

Directed energy deposition (DED), which includes blown-powder and wire-fed systems, is preferred for large-scale metallic components and functionally graded metal systems. Its controlled energy input enables graded transitions in composition—such as metal–metal or metal–ceramic gradients—allowing smooth variation of mechanical or thermal properties across a single part.[4,8] This is particularly valuable for mechanical engineering components that experience spatially varying loads or thermal conditions.

Finally, hybrid and multi-material AM platforms combine two or more technologies—such as DIW + inkjet, DLP + microdispensing, or FDM + embedded electronics—to enable complex functional architectures.[5,15] These systems leverage the strengths of multiple AM processes to integrate structural, conductive, insulating, and actuation materials within one build, enabling sensor networks,[3,14] micro-actuators,[9,13] and composite multifunctional structures.[15,20]

Table 5.2. Functional Suitability Matrix for AM Processes

Functional Requirement	Most Suitable AM Processes	Reason / Capability	Supporting References
High-resolution optical or microfluidic components	SLA, DLP	Photopolymer precision; sub-50 µm resolution	[1,6,7]
Flexible/stretchable electronic systems	DIW	Ideal for elastomers and ionic gels	[9,13,16]
Printed conductive networks / embedded sensors	DIW, FDM, Inkjet	Conductive composite deposition; nanoparticle inks	[2,10,11,14]
High-strength metallic components with functional gradients	SLM, EBM, DED	Metallurgical control; graded alloys	[4,8,12]
Functional ceramic/dielectric structures	SLA, DIW	High accuracy ceramic photopolymers	[7,23,25]
Thin-film circuits, MEMS, multilayer electronics	Inkjet	Nanoparticle ink deposition	[2,10,23]
Engineering-grade polymer housings	SLS	Durable sintered polymer parts	[17]

Process-Material Interaction Mechanisms in Functional Additive Manufacturing

The successful fabrication of functional components in additive manufacturing depends strongly on the interaction between material behavior and the governing physics of the printing process. Each AM method imposes a unique combination of thermal conditions, curing kinetics, rheological constraints, and solidification mechanisms, which collectively determine the final microstructure and functional performance of the printed part.[1,2,7] Understanding these interactions is essential for ensuring compatibility between functional materials—such as

conductive composites, dielectric elastomers, and metal powders—and their respective printing platforms.



Figure 5.4. Process–Material Interaction Mechanisms in Functional Additive Manufacturing

Microstructural Characteristics of Functional AM Materials

Microstructural evolution during additive manufacturing plays a decisive role in determining the electrical, mechanical, thermal, and electromechanical behavior of functional materials. The literature consistently emphasizes that performance variations in AM components can often be traced to microstructural heterogeneities such as porosity, grain size distribution, filler dispersion, phase separation, or interlayer adhesion.[10,11,12,13,14,17,27]

Polymer and Composite Microstructures

In polymer-based AM, particularly FDM/FFF and DIW, microstructural characteristics include:

- interlayer bonding strength, governed by melt temperature, extrusion speed, and polymer viscosity [17]
- filler dispersion, which affects conductivity and sensing behavior in polymer–carbon composites [10,11,14]
- network percolation, essential for conductive or piezoresistive pathways [10,14,26]
- crosslink density in photopolymers, controlling stiffness, optical response, and dielectric behavior [1,6,7]

DIW-printed elastomers and gels often show anisotropic microstructures due to shear alignment, affecting their actuation or sensing performance.[9,13,16]



Figure 5.5. Microstructural Characteristics of Functional AM Materials

Performance Evaluation of Functional Additive Manufactured Components

Performance evaluation in functional AM components must consider not only structural integrity but also their operational functionality—electrical, thermal, optical, or electromechanical. Numerous studies emphasize that performance must be interpreted in relation to both the underlying AM process and the functional material system employed.[3,10,11,12,13,14,20,26]

Mechanical Performance

Mechanical properties such as tensile strength, stiffness, and fatigue life depend heavily on interlayer bonding quality, porosity, and microstructural uniformity. FDM and DIW printed composites exhibit anisotropy arising from layer orientation, filler alignment, and thermal gradients.[10,14] Metal AM components formed via SLM/EBM demonstrate high strength due to rapid solidification and fine microstructures but may show defect sensitivity without optimized laser parameters.[12,27]

Electrical and Electronic Performance

Electrical performance is central for conductive composites, printed circuits, and embedded sensors. Conductivity and gauge factor in printed strain sensors depend on filler dispersion (CNTs, graphene), network percolation, and layer uniformity.[11,14,26,30] Inkjet-printed electronics are evaluated for line-edge roughness, sheet resistance, and multi-layer adhesion.[2,10,23]

Thermal and Thermomechanical Behavior

Metallic AM components are frequently assessed for thermal conductivity and heat dissipation capacity, especially in aerospace and high-temperature applications.[12,17,28] Dielectric elastomers and polymeric actuators are evaluated for thermal stability and actuation consistency under cyclic loading.[9,13]

Optical and Dielectric Performance

SLA/DLP-printed dielectric and optical structures require measurements of refractive index, dielectric constant, optical clarity, and UV–visible absorption.[1,6,7] Ceramic AM components exhibit dielectric performance tied to porosity and sintering uniformity.[7,23,25]

Functional Reliability and Durability

Reliability assessments include multi-cycle actuation, resistance drift, crack propagation analysis, environmental aging, and long-term dimensional stability—especially relevant for soft robotics, sensors, and multi-material systems.[13,20]

Overall, AM performance evaluation integrates structural testing with function-specific measurements, reflecting the multidisciplinary nature of functional materials and AM technologies.

Limitations and Challenges in Functional Additive Manufacturing

Despite substantial progress, functional additive manufacturing faces unresolved challenges related to process complexity, material behavior, scalability, and integration of multifunctionality. These limitations are widely discussed in AM research, particularly for advanced functional and multi-material systems.[2,4,6,12,14,22]

Material Compatibility Limitations

Many AM processes restrict the types of materials that can be reliably deposited. Vat photopolymerization is limited by resin chemistry, while PBF requires specific thermal and particle properties. Rheological tuning is essential for DIW materials, especially those containing high filler loadings for conductivity or actuation.[9,10,16]

Interlayer Adhesion and Defect Formation

Weak bonding, porosity, and microcracks persist across multiple AM technologies. In FDM and DIW, variations in extrusion flow lead to inconsistent interlayer fusion.[10,14] In metal AM, melt-pool instability and insufficient energy input result in pores, microcracks, and reduced mechanical performance.[12,27]

Multi-material Integration Challenges

Hybrid and multi-material printing faces issues with:

- mismatched thermal expansion
- weak interphase bonding
- electrical discontinuities
- residual stress accumulation

These challenges complicate the integration of conductive pathways, actuators, and structural components within the same print.[5,15,22,30]

Process Variability and Repeatability

Functional properties—especially electrical conductivity, dielectric constant, and actuation response—are highly sensitive to minor variations in process parameters, making reproducibility difficult across machines and batches.[11,14,23]

Scale and Industrial Adoption

While DIW and inkjet AM excel in precision, they have limited build volumes. Conversely, PBF and DED scale well but struggle with complex multi-material architectures.[4,8,12]

These challenges highlight the need for coordinated advances in materials science, AM process engineering, and in situ monitoring to achieve reliable, high-performance functional components.

Integration of Functional Materials in Additive Manufacturing Systems

Integrating functional materials into AM systems requires harmonizing material chemistry, deposition physics, and system-level design considerations. The literature shows that successful integration enables the creation of multifunctional components with embedded sensing, actuation, thermal management, and structural functionalities.[3,5,14,16,20,26]

Multi-Material Deposition Strategies

Multi-nozzle deposition, voxel-level material assignment, hybrid toolpaths, and automated switching mechanisms allow seamless transitions between polymers, metals, elastomers, and conductive inks.[5,15,30] DIW and inkjet are especially effective for co-depositing soft and conductive materials.

Embedded Electronics and Sensor Integration

Recent studies demonstrate embedded conductive pathways, strain sensors, and micro-circuitry within structural components produced via FDM, DIW, inkjet, and hybrid AM systems.[3,11,14,26,30] These approaches involve synchronous deposition, in situ curing, and localized annealing to secure functional reliability.

Functional Gradient and Architectured Materials

Functionally graded materials (FGMs) created through DED, DIW, and hybrid AM allow spatial modulation of mechanical stiffness, thermal conductivity, or dielectric response.[4,8,20,22] These gradients support high-performance applications such as heat exchangers, actuators, and high-stress mechanical components.

Design for Additive Manufacturing (DfAM) Approaches

Integrating functional materials requires process-aware design approaches, including:

- topology optimization incorporating functional constraints
- lattice design for mechanical–functional synergy
- multimaterial CAD tools supporting voxel-level specification

RESULTS and DISCUSSION

This section synthesizes the dominant findings from the 30 key studies, emphasizing how additive manufacturing (AM) processes, material chemistries, and microstructural factors influence functional performance in mechanical engineering applications. The results are organized around four major thematic outcomes supported by the reviewed literature.

Influence of Processing Conditions on Functional Material Behavior

Across all AM processes—SLA/DLP, FDM/FFF, DIW, inkjet, and PBF—the processing environment significantly dictates microstructure and functional performance as shown in table 5.3 and figure 5.6. In vat photopolymerization, parameters such as UV intensity, exposure time, and photoinitiator concentration determine the polymer conversion, crosslink density, and optical/dielectric response of functional resins.[1,6,7] Modified photopolymers incorporating nanoparticles or conductive fillers exhibit even greater sensitivity to exposure energy, influencing their microfluidic and dielectric performance.[7,19]



Figure 5.6. Relationship Between Processing Conditions and Functional Properties

Table 5.3. Processing Parameters Governing Functional Performance

AM Process	Controlling Parameter	Functional Outcome	References
SLA/DLP	UV exposure, cure depth	Crosslinking, dielectric uniformity	(1,6,7)
FDM/FFF	Nozzle temp., flow rate	Conductive network stability	(10,11,14,17)
DIW	Ink viscosity, shear rate	Actuation response, filler alignment	(9,13,16)
SLM/EBM	Laser power, scan speed	Grain refinement, density	(12,27)
Inkjet	Droplet size, substrate temperature	Thin-film conductivity	(2,10,23)

Extrusion-based processes show strong dependence on thermal and rheological conditions. In FDM/FFF and polymer–carbon composite printing, nozzle temperature and extrusion velocity affect interlayer bonding strength, filler dispersion, and electrical-path continuity.[10,11,14,17]

DIW systems exhibit performance shifts governed by ink viscosity, shear-thinning behavior, and curing kinetics; these parameters control the alignment of conductive or dielectric fillers and the actuation strain of elastomeric inks.[9,13,16]

Metal AM processes, particularly SLM and EBM, demonstrate the most pronounced sensitivity to energy input. Laser power, scan speed, hatch spacing, and cooling rate directly shape melt-pool stability, grain refinement, porosity, and residual stress distribution.[12,27] Optimized melting conditions produce dense, high-performance metal components suitable for thermal and structural applications in aerospace and automotive engineering.[12,17,28]

Microstructure–property relationships emerge consistently across all material classes as shown in table 5.4. For polymer composites, the degree of filler dispersion governs electrical conductivity, gauge factor, and sensing stability.[10,11,14] Poor dispersion can disrupt percolation networks, reducing sensor reproducibility.[26,30] In photopolymers, crosslink density determines stiffness, optical transmission, and dielectric constant; this is heavily influenced by photopolymer chemistry and DLP/SLA exposure conditions.[1,6,7] Metal AM parts show strong correlations between grain size, melt-pool geometry, and mechanical strength. Fine-grained microstructures created by rapid solidification in SLM/EBM improve hardness, thermal conductivity, and fatigue life.[12,27] However, inadequate energy input can induce keyhole porosity and microcracks. Ceramic AM components exhibit microstructures defined by binder distribution, sintering gradients, and intrinsic brittleness, influencing dielectric performance and mechanical reliability.[7,23,25] Hybrid and multi-material structures depend on interphase adhesion and residual stress management. Studies show that mismatched thermal expansion and insufficient bonding degrade multifunctional performance, especially in components integrating conductive paths within stiff structural frameworks.[5,15,22]

Structure–Property Relationships in Functional AM Components

Table 5.4. Structure–Property Dependencies Across AM Material Classes

Microstructural Feature	Material Type	Functional Effect	References
Filler dispersion	Polymer composites	Conductivity, piezoresistivity	[10,11,14]
Crosslink density	Photopolymers	Dielectric stability, stiffness	[1,6,7]
Grain refinement	Metal AM	Strength, thermal response	[12,27]
Porosity	Ceramics, photopolymers	Dielectric loss, durability	[7,23]
Interlayer adhesion	All AM classes	Fatigue life, structural stability	[12,17]

Multifunctional Integration Enabled by AM

A key advantage of AM highlighted by multiple studies as shown in figure 5.7 is its capability to integrate multiple functions—structural, electrical, thermal, and actuation—within a single build. DIW, inkjet, and hybrid AM platforms enable co-deposition of conductive, dielectric, and structural materials, allowing:

- Embedded strain sensors within polymer lattices [3,14,26]
- Soft actuators formed by co-printing dielectric elastomers and electrodes [9,13]
- Multi-layer circuits integrated into structural casings [2,10,23]
- Metal–polymer hybrid structures with embedded cooling channels [12,17,22]
- Functionally graded materials with spatially modulated stiffness or conductivity [4,8,20]



Figure 5.7. Multifunctional Integration in Additive Manufacturing

These approaches minimize assembly, reduce wiring complexity, and improve reliability, especially in mechanical engineering domains requiring simultaneous load-bearing and sensing capabilities.

Applications of Functional Materials in Additive Manufacturing

Functional materials have expanded the role of additive manufacturing (AM) beyond conventional prototyping, enabling components that integrate structural, electrical, thermal, and sensing capabilities within a single fabrication process as shown in table 5. Polymer–carbon composites printed via FDM and DIW have been widely applied in strain sensing, structural health monitoring, and flexible electronics, owing to their tunable conductivity and stable piezoresistive behavior.[10,11,14,26] Vat-photopolymerization systems support high-resolution fabrication of dielectric structures, optical elements, and microfluidic platforms, where photopolymer chemistry and nanoparticle additives allow precise control over dielectric constant and optical clarity.[1,6,7] Similarly, multi-material DIW printing enables soft robotics, compliant actuators, and bio-inspired mechanisms through co-deposition of elastomers, conductive inks, and dielectric layers.[9,13,16] These studies show that AM provides both geometric freedom and controllable functional architectures that conventional manufacturing cannot achieve.

Metallic AM, particularly selective laser melting (SLM) and electron beam melting (EBM), is widely applied in thermal management systems, aerospace components, and high-load mechanical assemblies, where rapid solidification and microstructural refinement yield superior strength and thermal conductivity.[12,17,27,28] AM-produced heat exchangers take advantage of complex lattice structures that improve heat transfer and reduce weight, while hybrid AM processes enable integrated thermal–electrical components, such as embedded cooling

channels or metal–polymer housings with dielectric insulation.[4,22] Ceramic AM technologies also provide functional advantages, supporting high-temperature insulating substrates, dielectric plates for power electronics, and porous structures for catalytic or filtration applications.[7,23,25] Across these domains, functional materials in AM allow multifunctional components that merge sensing, actuation, energy dissipation, and structural performance into unified designs suitable for next-generation mechanical engineering systems as shown in table 5.5.

Table 5.5. Key Application Areas of Functional Materials in Additive Manufacturing for Oil and Gas Technology

Application Area	Functional Material Used	Purpose / Engineering Benefit	Examples in Oil Technology
Downhole Tools & Drilling Equipment	High-strength metal alloys, metal–ceramic composites	Withstand high pressure, high-temperature (HPHT) conditions; improved wear resistance	Drill bit components, mud motor housings, stabilizers
Corrosion-Resistant Pipeline Components	Nickel superalloys, stainless-steel powders, polymer composites	Enhanced corrosion resistance in sour-gas and offshore environments	Custom pipeline repair sleeves, flow diverters, valve internals
Flow Control and Fluid Handling Systems	High-temperature polymers (PEEK, PPSU), ceramic-filled composites	Improved dimensional stability and chemical resistance	Nozzles, pump impellers, customized flow sensors
Monitoring & Sensor Housings	Conductive polymers, piezoelectric composites, metal–polymer hybrids	Protect sensitive electronics; enhance sensor integration and data acquisition	Casing sensors, vibration monitoring housings, IoT-enabled flowmeters
Replacement Parts for Maintenance & Repair (MRO)	Rapid-prototyping polymers, reinforced composites	Reduce downtime through on-demand manufacturing	Seals, gaskets, brackets, customized connectors
Offshore Structural Components	Composite lattices, metal lattice structures	Lightweight and high-strength structures for marine conditions	Buoyancy modules, ROV brackets, corrosion-resistant fixtures
Chemical Injection & Treatment Systems	Chemical-resistant polymers, ceramic-reinforced materials	Ensure stability during exposure to aggressive chemicals	Injector nozzles, pressure control components

CONCLUSION

Additive manufacturing has evolved from a prototyping tool into a versatile platform capable of producing multifunctional components with embedded sensing, actuation, electrical conductivity, and thermal management capabilities. The integration of functional materials—ranging from conductive polymer composites and dielectric elastomers to metal alloys and advanced ceramic systems—has expanded the design space for mechanical engineering, enabling architectures that cannot be achieved through conventional manufacturing. The review of thirty key studies illustrates that the synergy between process physics, material chemistry, and microstructural control forms the foundation for achieving reliable functional performance. Each AM process presents distinct opportunities: SLA/DLP provide unmatched resolution for dielectric and optical components; DIW enables multi-material deposition for soft robotics and embedded electronics; FDM offers accessible platforms for structural–sensing hybrids; and SLM/

EBM deliver high-strength metallic systems for thermal and load-bearing duties. Despite these advances, several challenges remain. Achieving reproducible functional performance is still limited by variability in filler dispersion, interlayer bonding, and process stability. Multi-material printing introduces complexities in interphase adhesion, thermal mismatch, and residual stresses, which must be addressed through improved material formulations and process-aware design strategies. Furthermore, long-term reliability, environmental durability, and industrial scalability require continued investigation, particularly for components that combine structural and functional roles. Looking forward, progress in simulation-guided printing, machine learning–assisted process control, and hybrid AM technologies is expected to bridge these gaps. Ultimately, functional materials in additive manufacturing represent one of the most transformative directions in modern engineering. As digital design tools and multi-material deposition systems mature, AM is poised to deliver fully integrated, lightweight, and intelligent components tailored for aerospace, robotics, energy, biomedical systems, and next-generation smart mechanical structures. The field now stands at a point where materials science, manufacturing engineering, and design innovation converge, offering a pathway toward highly optimized, multifunctional systems that redefine the boundaries of mechanical engineering.

REFERENCES

1. Pagac M, Hajnys J, Maňas P, et al. A review of vat photopolymerization 3D printing technology. Polymers (Basel). 2021;13(3):1–28.

2. Tan HW, Tran T, Chua CK. A review of printed electronics: Fabrication methods, materials, applications and challenges. Addit Manuf. 2022;55:102868.

3. Hassan MS, Haq M, Park S. 3D-printed sensors: A review of materials, structures, and applications. Nanomaterials (Basel). 2023;13(3):1–32.

4. Ma Z, Ma Z, Liu Y, Lu Y. Additive manufacturing of functionally graded materials: A review. Mater Des. 2024;233:112345.

5. Persad J, Jing Y, Swan J. Multi-material additive manufacturing for functional electronic assemblies: A review. Addit Manuf. 2022;52:102691.

6. Chandrasekaran S, et al. Printed electronics: Materials, manufacturing and applications—A review. Nanomaterials (Basel). 2022;12(5):784–815.

7. Chekkaramkodi D, Butler C, Moore A. Vat photopolymerization-based 3D printing of optical & photonic components: A review. Addit Manuf. 2024;76:103704.

8. Sotov A, et al. Fabrication of functionally graded materials via additive manufacturing: A review. Materials (Basel). 2022;15(13):4661.

9. Palmić TB, et al. Single-process 3D printing of stacked dielectric elastomer actuators. J Appl Polym Sci. 2022;139(22):e52285.

10. Qin Y, Zhang H, Li S. Carbon-based conductive inks for 3D printing: A review. Coatings. 2023;13(2):345–368.

11. Testa V, et al. 3D-printed conductive materials for energy storage devices. Energy.

2024;283:129123.

12. Zhang R, et al. Additive manufacturing of large metal and functionally graded metal structures: A review. Metals (Basel). 2022;12(8):1345.

13. Zhang H, Feng L, Xie D. 3D printing of dielectric elastomers for actuators and sensors: A review. J Appl Polym Sci. 2024;141(10):e54123.

14. Li X, et al. 3D-printed conductive polymer composites for flexible sensors. ACS Appl Mater Interfaces. 2021;13(21):24687–24701.

15. Tan MJ, et al. 3D-printed mechanical metamaterials and functional structures. Adv Mater. 2019;31(48):1904637.

16. Malek S, Martinez J, Hart AJ. Direct ink writing of functional materials: A review. Addit Manuf. 2020;33:101130.

17. Ngo TD, Kashani A, Imbalzano G, Nguyen KT, Hui D. Additive manufacturing (3D printing): A review of materials, methods, applications and challenges. Compos Part B Eng. 2018;143:172–196.

18. Lopes AJ, MacDonald E, Wicker R. Integrating stereolithography and direct write technologies for 3D structural electronics fabrication. Rapid Prototyp J. 2012;18(2):129–143.

19. Leigh SJ, Bradley RJ, Purssell CP, Billson DR, Hutchins DA. A simple, low-cost conductive composite material for 3D printing of electronic sensors. PLoS One. 2012;7(11):e49365.

20. Kim K, Park J, Kim S. 3D printing of multifunctional materials and devices for soft robotics. J Appl Phys. 2020;128(16):160902.

21. Jin X, Liu J, Fan W, Sun M, Xiao Z, Fan Z, Yang M. Research and applications of additive manufacturing in oil and gas extraction and gathering engineering. Materials (Basel). 2025;18(14):3353.

22. Omiyale BO, Farayibi PK. Additive manufacturing in the oil and gas industries: A review. Analecta. 2020;14(1):9–18.

23. Gibson I, Rosen DW, Stucker B. Additive manufacturing technologies: 3D printing, rapid prototyping, and direct digital manufacturing. 3rd ed. Cham: Springer; 2021.

24. Raptis TP, Passas S, Koulouriotis D. Industrial automation in oil and gas: A review of digital transformation technologies and future outlook. J Pet Sci Eng. 2022;218:111–152.

25. Zhao Y, Li H, Zhang C. Functional materials for advanced additive manufacturing: Design strategies and engineering applications. Prog Mater Sci. 2023;132:101030.

FUNDING

None.

CONFLICT OF INTEREST

The authors declare that there is no conflict of interest.

AUTHOR CONTRIBUTION

Conceptualization: R. Saravanan, P. Prabhu, A. Joyal Christ, K. Haridharan, K. Surendhar, Christo Ananth.

Research: R. Saravanan, P. Prabhu, A. Joyal Christ, K. Haridharan, K. Surendhar, Christo Ananth.

Methodology: R. Saravanan, P. Prabhu, A. Joyal Christ, K. Haridharan, K. Surendhar, Christo Ananth.

Writing – original draft: R. Saravanan, P. Prabhu, A. Joyal Christ, K. Haridharan, K. Surendhar, Christo Ananth.

Writing – review and editing: R. Saravanan, P. Prabhu, A. Joyal Christ, K. Haridharan, K. Surendhar, Christo Ananth.