South American Publishing

SAP Multidisciplinary Open. 2025; 3:194
doi: 10.62486/mo2025194

ORIGINAL

Perovskite Reimagined: A Comprehensive Exploration of Its Influence on Ceramic Science and Technology

Perovskita Reinterpretada: Una Exploración Integral de su Influencia en la Ciencia y Tecnología de Cerámicos

Md Tanweer Alam[1] ✉, Awadesh Prasad[1]

[1]University Department of Physics, V. K. S. University, Ara-802301 Bihar, India.

Cite as
Alam MT, Prasad A. Perovskite Reimagined: A Comprehensive Exploration of Its Influence on Ceramic Science and Technology. SAP Multidisciplinary Open. 2025; 3:194. https://doi.org/10.62486/mo2025194

Publication History
Submitted: 07-05-2024
Revised: 22-09-2024
Accepted: 20-03-2025
Published: 21-03-2025

Corresponding Author
Md Tanweer Alam ✉

ABSTRACT

Introduction: the perovskite structure, characterized by the general formula ABX_3, has been a cornerstone in ceramic science and technology due to its remarkable versatility and adaptability. From the earliest insights of Goldschmidt linking material structure to composition, the perovskite structure emerges as a quintessential demonstration of this principle.
Objective: this paper aims to offer a thorough review of perovskite materials, emphasizing the interplay between their structural versatility and practical utility.
Results: known for its remarkable adaptability, the perovskite framework can accommodate a vast array of compositional variations, enabling the creation of materials with diverse properties such as dielectric, conductive, and superconductive behaviors. Among these, barium titanate ($BaTiO_3$) stands out as a prime example of a perovskite that can be fine-tuned to achieve enhanced dielectric characteristics, leading to widespread industrial usage. The capacity of perovskites to endure extreme environmental conditions, including the immense pressures found in Earth's interior, underscores their relevance not only in technology but also in geological research. Recent explorations into piezoelectric and ferroelectric applications highlight the cutting-edge potential of these materials for future innovations. By adjusting perovskite compositions, researchers can systematically optimize functionalities across multiple sectors, ranging from consumer electronics to advanced scientific instrumentation.
Conclusion: through an examination of novel findings, the authors shed light on the continuing evolution of perovskite research, illuminating both the foundational science and the growing array of real-world applications and future directions.

Keywords: Perovskite Structure; Piezoelectric; Ferroelectric; Electronic Devices.

RESUMEN

Introducción: la estructura perovskita, caracterizada por la fórmula general ABX_3, ha sido un pilar en la ciencia y tecnología de cerámicas debido a su versatilidad y adaptabilidad excepcionales. Desde los primeros postulados de Goldschmidt, que relacionaban la estructura de los materiales con su composición, la perovskita surge como un ejemplo paradigmático de este principio.
Objetivo: este artículo ofrece una revisión exhaustiva de los materiales perovskíticos, destacando la relación entre su versatilidad estructural y su utilidad práctica.
Resultados: conocida por su notable flexibilidad, esta estructura puede albergar una amplia variedad de variaciones composicionales, permitiendo diseñar materiales con propiedades diversas, como comportamiento dieléctrico, conductor o superconductor. Entre estos, el titanato de bario ($BaTiO_3$) destaca como un ejemplo clásico de perovskita cuyas propiedades dieléctricas pueden ajustarse para aplicaciones industriales. Su capacidad para resistir condiciones ambientales extremas, como las altas presiones del interior terrestre, resalta su relevancia no solo tecnológica, sino también geológica. Investigaciones recientes en aplicaciones piezoeléctricas y ferroeléctricas subrayan el potencial innovador de estos materiales. Mediante el ajuste composicional, los investigadores pueden optimizar sistemáticamente sus funcionalidades en sectores que abarcan desde la electrónica de consumo hasta instrumentación científica avanzada.
Conclusión: a través del análisis de hallazgos recientes, los autores exploran la evolución continua de la investigación en perovskitas, abordando tanto sus fundamentos científicos como sus crecientes aplicaciones y futuras direcciones.

Palabras clave: Estructura Perovskita; Piezoeléctrico; Ferroeléctrico; Dispositivos Electrónicos.

© 2025; The Authors. This Open access article is distributed under the Creative Commons Attribution 4.0 license (https://creativecommons.org/licenses/by/4.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

INTRODUCTION

Perovskite materials trace their origins to a noteworthy discovery in 1839, when the German mineralogist Gustav Rose first encountered an unusual calcium titanate mineral ($CaTiO_3$) in the Ural Mountains of Russia. Recognizing its distinctive properties, Rose named this newly identified mineral perovskite in honor of Russian mineralogist Lev Perovski (1792–1856) (Bhalla, Guo, & Roy 2000; Rose 1839).[1] Over time, the term "perovskite" has been used to designate not only the specific natural mineral but also an entire family of compounds characterized by the ABX_3 crystal structure, which shares similar structural motifs to the original $CaTiO_3$ mineral (Goldschmidt 1926; Imada, Fujimori, & Tokura 1998).[2] Although the name "perovskite" was initially tied to a single naturally occurring mineral, the structure's scientific significance became more evident as crystallographers and mineralogists systematically explored the relationship between ionic sizes, crystal chemistry, and physical properties. Early in the 20th century, Victor Goldschmidt extensively investigated how ionic radii governed structural stability in oxides, laying the groundwork for understanding why perovskite-based compounds could accommodate numerous chemical substitutions (Goldschmidt 1926; Müller 1993).[3] This notion of "tolerance" proved fundamental in explaining the wide compositional latitude of perovskites, which, in turn, made them highly valuable for research in ceramics, electronic devices, and more.

Ideal Perovskite Structure

At its simplest, the perovskite structure can be described by the general formula ABX_3, where "A" typically refers to a larger cation, "B" designates a smaller cation (often a transition metal), and "X" is an anion (commonly oxygen, but it can also be a halide or other species). In the idealized cubic form (space group $Pm\bar{3}m$), the **A** cation occupies the corners of the cubic lattice, the **B** cation resides at the body center, and the **X** anions sit at the face centers (Bhalla et al. 2000; Mitzi 2004)[1]. More specifically:

1. The A-site cation is surrounded by twelve anions, forming a dodecahedral coordination environment.
2. The B-site cation sits in the center of an octahedron of anions, meaning it has six nearest-neighbor anions.
3. The X anions effectively bridge the A and B sites, ensuring a stable three-dimensional network of corner-sharing BX_6 octahedra.

This configuration—A cation in a 12-fold site, B cation in a 6-fold site, and X anion bridging the two—permits remarkable flexibility. One reason is the ability to substitute different elements at the A and B sites, significantly altering electrical, magnetic, optical, and mechanical properties (Müller 1993; Imada et al. 1998).[4]

Compositional Flexibility and Tolerance Factor

A hallmark of the perovskite family is their extraordinary compositional adaptability. This adaptability arises from a concept known as the tolerance factor (t), introduced by Goldschmidt (1926).[3]

Mathematically expressed as:

$$t = \frac{r_A + r_X}{\sqrt{2}(r_B + r_X)},$$

$$t = \frac{r_A + r_X}{\sqrt{2}(r_B + r_X)},$$

Where r_A is the ionic radius of the A-site cation, r_B is that of the B-site cation, and r_X is that of the anion. A tolerance factor close to 1 (typically between 0,8 and 1,0) suggests a stable cubic structure, while deviations can lead to lower-symmetry variants (orthorhombic, tetragonal, or rhombohedral). This phenomenon is crucial in ceramic science because even slight ionic substitutions can drastically change phase stability and material properties (Bhalla et al. 2000).[1]

For instance, if the A cation is smaller than the ideal size, the BX_6 octahedra may tilt, giving rise to orthorhombic or rhombohedral distortions (Glazer 1972; Müller 1993).[4] On the other hand, if the A cation is larger or the B cation is smaller, the structure may adopt hexagonal or layered variants, demonstrating just how profoundly compositional changes can modify structural symmetry.

Role in ceramic science and technology

Dielectrics and ferroelectrics

Perhaps one of the most famous perovskite oxides in ceramic science is barium titanate ($BaTiO_3$). Discovered to exhibit ferroelectricity, $BaTiO_3$ sparked a revolution in electroceramics, leading to applications in capacitors, piezoelectric actuators, transducers, and more (Jaffe, Cook, & Jaffe 1971).[5] Its high dielectric constant and polarization behavior exemplify how the perovskite structure can be manipulated for advanced functionalities.

Superconductivity

The discovery of high-temperature superconductivity in copper-oxide perovskites, such as yttrium barium copper oxide ($YBa_2Cu_3O_{7-\delta}$), expanded interest in the perovskite family (Bednorz & Müller 1986). The layered perovskite blocks in these compounds facilitate superconductivity at relatively higher temperatures than conventional metallic superconductors, underscoring

the structural influence on electronic properties.

Magnetic and Colossal Magnetoresistance (CMR)

Manganese-based perovskites, such as $La_{1-x}Sr_xMnO_3$, exhibit colossal magnetoresistance, where electrical resistance changes dramatically under an applied magnetic field (Tokura 2006).[6] This phenomenon has implications for magnetic sensors, data storage, and spintronic devices. Once again, the perovskite lattice is central to enabling doping strategies that optimize these magnetic and electrical behaviors.

Fuel Cells and Catalysis

Certain perovskite oxides (e.g., $La_{1-x}SrxMnO_3$) are used as cathodes in solid oxide fuel cells (SOFCs), capitalizing on their mixed ionic and electronic conductivity. In addition, perovskites such as $LaCoO_3$ or $LaFeO_3$ can serve as catalysts for various oxidation reactions. Their structural stability at high temperatures and flexible compositional range make them valuable in energy and environmental technologies (Mogensen, Sammes, & Tompsett 2000).[7]

Photovoltaics

Organic-inorganic halide perovskites (e.g., $CH_3NH_3PbI_3$) have risen to prominence in solar cell research due to their exceptional light absorption and carrier transport properties (Snaith 2013)[8]. Although the original perovskite mineral was an oxide, the concept of an ABX_3 lattice extends to halides, broadening the scope of applications well beyond traditional ceramics.

Structural distortions and advanced ceramics

Ceramic technology often relies on the controlled manipulation of crystal structures to optimize mechanical, thermal, and electronic properties. The perovskite structure's capacity for structural distortion can be both advantageous and challenging:

Advantage: Structural distortions can induce ferroelectric or multiferroic properties, allowing materials to exhibit simultaneous magnetic and electric order (Cheong & Mostovoy 2007).[9] This synergy is pivotal in developing new transducer materials, memory devices, and sensors.

Challenge: Distortions can complicate sintering processes or degrade performance at high temperatures. Researchers frequently employ doping strategies or composite formulations to mitigate undesired phase transitions, ensuring stable performance over a broad temperature range (Guo, Cross, & Park 2001).[10]

Recent advances in perovskite ceramics: synthesis, processing, and applications

Perovskite ceramics have emerged as a groundbreaking class of materials, capturing significant attention in the fields of materials science, energy, and electronics due to their unique structural, electrical, and optical properties. The term "perovskite" refers to a family of materials with the general chemical formula ABX_3, where A and B are cations of different sizes, and X is an anion, typically oxygen or a halogen. The versatility of perovskite ceramics lies in their ability to accommodate a wide range of elements, enabling tailored properties for specific applications. Recent advancements in the synthesis, processing, and application of perovskite ceramics have opened new avenues for innovation, particularly in energy storage, catalysis, and optoelectronics.




Figure 1. Schematic illustration of the sensory applications of perovskite nanomaterials.[11]

Synthesis of Perovskite Ceramics

The synthesis of perovskite ceramics has undergone significant evolution, with researchers developing novel methods to achieve precise control over composition, morphology, and crystallinity. Traditional solid-state reaction methods, which involve high-temperature calcination of precursor powders, remain widely used due to their simplicity and scalability. However, these methods often result in inhomogeneous products with large grain sizes, limiting their performance in certain applications. To address these limitations, advanced synthesis techniques such as sol-gel processing, hydrothermal synthesis, and chemical vapor deposition (CVD) have been developed. The sol-gel method, for instance, offers excellent control over stoichiometry and particle size, producing homogeneous and fine-grained perovskite powders. This technique involves the hydrolysis and condensation of metal alkoxides

or salts, followed by thermal treatment to form the desired perovskite phase. Hydrothermal synthesis, on the other hand, utilizes high-pressure and high-temperature conditions in an aqueous environment to crystallize perovskite materials at relatively low temperatures. This method is particularly advantageous for synthesizing nanostructured perovskites with high surface areas, which are ideal for catalytic and sensing applications.

Chemical vapor deposition (CVD) has also gained prominence as a versatile technique for depositing high-quality perovskite thin films. By precisely controlling the precursor gases and deposition parameters, CVD enables the growth of uniform and defect-free films with tailored properties. These advancements in synthesis methods have not only improved the quality of perovskite ceramics but also expanded the range of achievable compositions and structures.

Processing Techniques for Enhanced Performance

The processing of perovskite ceramics plays a critical role in determining their final properties and performance. Recent innovations in processing techniques have focused on enhancing the density, purity, and microstructure of perovskite materials. Sintering, a key step in ceramic processing, has seen notable improvements through the adoption of advanced methods such as spark plasma sintering (SPS) and microwave sintering. Spark plasma sintering (SPS) is a rapid sintering technique that applies pulsed electric currents and uniaxial pressure to achieve high-density ceramics at lower temperatures and shorter times compared to conventional sintering. This method minimizes grain growth and preserves the nanoscale features of perovskite materials, making it particularly suitable for producing ceramics with enhanced mechanical and electrical properties. Microwave sintering, another emerging technique, utilizes microwave radiation to heat the material volumetrically, resulting in uniform heating and reduced processing times. In addition to sintering, additive manufacturing (3D printing) has emerged as a transformative approach for processing perovskite ceramics. By enabling the fabrication of complex geometries and customized structures, 3D printing has expanded the design possibilities for perovskite-based devices. Techniques such as direct ink writing (DIW) and stereolithography (SLA) have been successfully employed to create perovskite components with precise control over shape and porosity.

Applications of Perovskite Ceramics

The unique properties of perovskite ceramics have led to their widespread adoption in a variety of applications, ranging from energy storage and conversion to environmental remediation and biomedical devices. One of the most prominent applications is in the field of energy storage, where perovskite-based materials are used as electrodes in solid oxide fuel cells (SOFCs) and lithium-ion batteries. The high ionic conductivity and thermal stability of perovskite ceramics make them ideal candidates for these applications, enabling efficient energy conversion and storage.

In the realm of catalysis, perovskite ceramics have demonstrated exceptional performance as catalysts and catalyst supports for various chemical reactions. Their tunable electronic structure and redox properties allow for the optimization of catalytic activity and selectivity. For example, perovskite oxides such as $LaCoO_3$ and $SrTiO_3$ have been widely studied for their ability to catalyze oxygen reduction and evolution reactions, which are critical for water splitting and fuel cell technologies.

Perovskite ceramics have also made significant strides in optoelectronics, particularly in the development of solar cells and light-emitting diodes (LEDs). Organic-inorganic hybrid perovskites, such as methylammonium lead iodide ($MAPbI_3$), have achieved remarkable power conversion efficiencies in photovoltaic devices, rivaling those of traditional silicon-based solar cells. The tunable bandgap and high absorption coefficient of these materials make them highly attractive for next-generation solar energy harvesting. In addition to energy-related applications, perovskite ceramics have found use in environmental remediation, where they are employed as adsorbents and photocatalysts for the removal of pollutants from air and water. Their ability to degrade organic contaminants under light irradiation has positioned them as promising materials for sustainable environmental solutions.




Figure 2. Different perovskite materials and their applications

Challenges and future directions

Despite the remarkable progress in the synthesis, processing, and application of perovskite ceramics, several challenges remain to be addressed. One of the primary concerns is the stability of perovskite materials, particularly under harsh operating conditions such as high temperatures and humid environments. For instance, hybrid perovskites used in solar cells are prone to degradation

due to moisture and thermal stress, limiting their long-term performance and commercial viability. To overcome these challenges, researchers are exploring strategies such as compositional engineering, surface passivation, and encapsulation to enhance the stability of perovskite materials. Additionally, the development of lead-free perovskites is gaining traction as a means to address the environmental and health concerns associated with lead-based compounds. Another area of focus is the scalability of synthesis and processing techniques. While laboratory-scale methods have demonstrated impressive results, translating these advancements to industrial-scale production remains a significant hurdle. Efforts are underway to optimize manufacturing processes and reduce costs, paving the way for the widespread adoption of perovskite ceramics in commercial applications.

CONCLUSION

Recent advances in the synthesis, processing, and application of perovskite ceramics have positioned these materials as key enablers of innovation across multiple disciplines. From energy storage and catalysis to optoelectronics and environmental remediation, perovskite ceramics offer unparalleled versatility and performance. While challenges related to stability and scalability persist, ongoing research and development efforts are expected to unlock new possibilities and drive the commercialization of perovskite-based technologies. As the field continues to evolve, perovskite ceramics are poised to play a pivotal role in shaping the future of materials science and engineering.

FINANCING

None.

CONFLICT OF INTEREST

None.

AUTHOR CONTRIBUTIONS

Conceptualization: Md Tanweer Alam, Awadesh Prasad.
Investigation: Md Tanweer Alam, Awadesh Prasad.
Methodology: Md Tanweer Alam, Awadesh Prasad.
Drafting - original draft: Md Tanweer Alam, Awadesh Prasad.
Writing - review, editing: Md Tanweer Alam, Awadesh Prasad.

REFERENCES

1. Bhalla AS, Guo R, Roy R. The perovskite structure—a review of its role in ceramic science and technology. Mater Res Innov. 2000;4(1):3–26.

2. Swierczek K, Gozu M. Structural and electrical properties of selected La1-x Sr x Co0. 2Fe0. 8O3 and La0. 6Sr0. 4Co0. 2Fe0. 6Ni0. 2O3 perovskite type oxides. J Power Sources. 2008;173(2):695–9.

3. Goldschmidt VM. Über das krystallochemische und geochemische Verhalten des Germaniums. Naturwissenschaften. 1926;14(14):295–7.

4. Müller WA, Leitz T. Metamorphosis in the Cnidaria. Can J Zool. 2002;80(10):1755–71.

5. Jaffe B, Cook WR, Jaffe H. The piezoelectric effect in ceramics. Piezoelectric Ceram. 1971;7–21.

6. Tokura Y. Multiferroics as quantum electromagnets. Science (80-). 2006;312(5779):1481–2.

7. Mogensen M, Sammes NM, Tompsett GA. Physical, chemical and electrochemical properties of pure and doped ceria. Solid state ionics. 2000;129(1–4):63–94.

8. Liu M, Johnston MB, Snaith HJ. Efficient planar heterojunction perovskite solar cells by vapour deposition. Nature. 2013;501(7467):395–8.

9. Cheong SW, Mostovoy M. Multiferroics: a magnetic twist for ferroelectricity. Nat Mater. 2007;6(1):13–20.

10. Noheda B, Cox DE, Shirane G, Park SE, Cross LE, Zhong Z. Polarization rotation via a monoclinic phase in the piezoelectric 92% PbZn 1/3 Nb 2/3 O 3-8% PbTiO 3. Phys Rev Lett. 2001;86(17):3891.

11. Shellaiah M, Sun KW. Review on sensing applications of perovskite nanomaterials. Chemosensors. 2020;8(3):55.